

MasterEmaco[®] S 822CI

Cementitious spray applied repair mortar for cathodic protection overlays

MATERIAL DESCRIPTION

MasterEmaco S 822CI is a ready-to-use, cement based shotcrete mix with reduced rebound for cathodic overlays. It is specially designed for civil and mining applications using either the wet or dry shotcreting systems.

AREAS OF APPLICATION

Repairs to the underside of bridge decks, bridge piers and beams, tunnels, drains, sea walls, and culverts where impressed current cathodic protection systems are used.

CHARACTERISTICS AND BENEFITS

- Factory mixed - no onsite variations
- Easy to use - requires only the addition of potable water for mixing or spraying
- Economical - reduces handling and clean-up costs and speeds up repairs
- Versatile - is easily sprayed using the wet mix shotcrete system or dry mix systems
- Good working time - over one hour at 21°C
- Low resistivity - improves effectiveness of impressed current cathodic protection systems
- Controlled shrinkage - reduced cracking tendency

PROPERTIES

Age	Compressive Strength MPa (AS1012.14)	Flexural Strength MPa (AS1012.11)
24 hours	30.0	
7 days	42.0	6.0
28 days	58.0	6.6
Permeability (Taywood Method)	1.4 x 10 ⁻¹² (metres/sec.)	

Electrical Resistivity (Taywood method)	
Age	Resistivity (Ohm cm)
19 days	14400
28 days	23500
41 days	44000

All performance data is determined by testing of actual, in-place shotcreted specimens such as cores and beams taken from test panels.

Reasonable variations from the data shown can be expected, depending on the care taken in evaluating test specimens, and jobsite conditions such as the quality of substrate preparation, level of expertise of the nozzleman, curing procedures and weather.

APPLICATION

Prepare the surface to be shotcreted by removing all unsound concrete, dirt, dust and debris. For structural repairs to existing concrete members, saturate the properly prepared concrete surface for a minimum of 7 hours prior to shotcreting.

Mix **MasterEmaco S 822CI** with approximately 1.8-2.5 litres of water per 20kg bag.

MasterEmaco S 822CI can be shotcreted in depths ranging from 10mm - 150mm in one pass.

CURING

Proper curing is extremely important. Wet curing is recommended for the first 3-5 days, after that time continue curing by the use of a quality curing compound such as **MasterKure 250**.

ESTIMATING DATA

One 20kg bag of **MasterEmaco S 822CI** mixed with water yields approximately 10.2 litres (0.0102m³). This will cover approximately 10m² at 1mm thick and a bag will be sufficient to apply approximately 10mm of shotcrete to a square meter.

MasterEmaco S 822CI				
L	Thickness in mm /m ²	m ³	bags /m ³	m ² /mm thickness
10.2	10.2mm	(0.0102)	98	10.2 m ²

Allowance must be made for rebound and cut off for finishing which will reduce the coverage accordingly.

Without allowing for cut-off, an allowance of 5-10% can be made for rebound. This is for an experienced nozzleman and ideal conditions. For overhead spraying the rebound allowance may be increased to 10-50% depending on the admixtures used. Contact your local Master Builders Solutions Technical Sales Representative for further advice

PACKAGING

MasterEmaco S 822CI is available in 20kg bags.

SHELF LIFE

MasterEmaco S 822CI has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

PRECAUTIONS

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

MasterEmaco[®] S 822CI

Cementitious spray applied repair mortar for cathodic protection overlays

DISCLAIMER

MasterEmaco-S822CI-ANZ-V8-1220

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 11 Stanton Road
 Seven Hills NSW 2147

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Freecall: 0800 334 877

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

® = registered trademark of a MBCC Group member in many countries of the world