

MasterFiber 051

Fibrillated polypropylene fibre micro-reinforcement system

Material Description

MasterFiber 051 is a fibrillated micro fibre for secondary concrete reinforcement.

MasterFiber 051 is engineered to reduce plastic and settlement cracking, improve impact strength, enhance fatigue resistance, and maximise concrete toughness.

This fibrillated fibre is manufactured to offer long term durability and secondary/temperature control.

The addition of micro fibrils attached to the primary fibre allow for additional anchorage sites providing a stronger fibre-to-matrix bond, as a result increased performance over non-fibrillated fibre.

MasterFiber 051 is non-corrosive, non-magnetic, chemically inert and 100% alkali proof.

Areas of Application

MasterFiber 051 is recommended for use in concrete applications such general purpose slab-on-grade, toppings, slope paving, driveways, basement floors etc.

MasterFiber 051 is TMR approved for use in extruded concrete mixes for jersey barriers, kerbs, and gutters where a ductile material is required.

MasterFiber 051 increases:

- Impact and shear resistance
- Fatigue and abrasion resistance
- Concrete toughness
- Long-term durability

MasterFiber 051 decreases:

- Plastic shrinkage
- Settlement cracking

Properties

MasterFiber 051 is a micro-fibrillated fibre.

Materials	100% virgin polypropylene
Form	Fibrillated
Colour	White
Dose Rate	0.9 kg/m ³
Length	51mm
Tensile Strength	450 MPa
Specific Gravity	0.91
Melting Point	Approx. 160 °C
Acid/alkali resistance	Excellent
Absorption	Nil
Compliance	EN14889.2

Dosage

The recommended dose rate for **MasterFiber 051** is 0.9 kg/m³.

Application

MasterFiber 051 can be added directly to the concrete mixing system during the batching of other materials.

For best results, **MasterFiber 051** should be added to the concrete mix before the batching process. The addition of **MasterFiber 051** should not require a change to the mix design but minor impact to flow and slump properties may occur.

Trials should be performed to determine performance and an appropriate mix design.

For more detailed mixing and dosing information, contact your Master Builders Solutions Technical Sales Representative.

Packaging

Bags	0.9 kg Mulchable
Carton	12 Bags
Pallet	27 Cartons

MasterFiber 05I

Fibrillated polypropylene fibre micro-reinforcement system

Storage

MasterFiber 05I should be stored undercover and protected from the weather.

Disclaimer

MasterFiber-05I-ANZ-V10-0623

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd

ABN 69 634 934 419
 Unit 102, 2 Burbank Place
 Norwest NSW 2153

Freecall: 1300 227 300

www.master-builders-solutions.com/en-au

MB Solutions New Zealand Ltd

45C William Pickering Drive
 Albany, Auckland
 New Zealand

Freecall: +64 9414 7233

Emergency Advice:

1300 954 583 within Australia (24hr)
 0800 001 607 within New Zealand

