

Page | of 2

MasterInject 1380

Structural concrete bonding process injection resin

Material Description

MasterInject 1380 is a two-component, solventless, lowviscosity liquid adhesive for pressure injection grouting. MasterInject 1380 was developed specifically for use with the Structural Concrete Bonding Process (SCBP) and is available only through certified applicators of this process.

Areas of Application

- Structurally re-bonding cracked concrete sections.
- Filling porous or honeycombed concrete or grout.
- Anchoring bolts, dowels and reinforcing bars.
- Grouting areas pre-packed with aggregate to form bearing supports.

Characteristics and Benefits

- Low viscosity excellent penetration of fine fissures.
- Resistance to creep and stress relaxation due to high heat deflection temperature.
- Fast cure rate fast return to loaded conditions.
- Bonds in wet and cold conditions excellent adhesion even under adverse conditions.

Properties

	Part A	Part B	Mixed	
Form	Liquid	Liquid	Liquid	
Colour	Clear	Black	Black	
Specific Gravity @	1200	1000	1130	
25°C,kg/m3				
Mixing Ratio (by volume)	2			
(by weight)	100	30		
Viscosity,cps @ 23°C	625			
Application temperature	8-35°C			
range				
Minimum cure	0°C			
temperature				
Properties of cured material Tested at 23°C				
Tensile strength, MPa (EN ISO 527-1; -2)			56	
Tensile elongation,% (EN ISO 527-1; -2)			4.4	
Flexural strength, N/mm ² (ASTM D790)			82.7	
Compressive strength (EN ISO 12190)			110	

Application

For **MasterInject 1380** SCBP injection resins, the crack faces inside the concrete are considered to be the "sub-strate". The substrate may be moist or even totally soaked with water, such as in water-filled cracks. Though the adhesion of the injection resin on water-saturated sub-strates will still be sufficient, a slight decrease of the adhe-sion characteristics as compared to applications in dry concrete will occur.

Substances preventing the proper adhesion of the resin to the substrate, such as oil, marine-growth, etc., have to be removed using appropriate techniques such as ultra-high pressure water jetting, flushing with detergents, etc. The resin is mixed and installed, using the model 20-3N injec-tion-equipment (or other suitable pressure injection equip-ment), which forms an integral part of the SCBP, available through Master Builders Solutions Approved Applicators only.

Estimating Data

Usage is dependent on the crack volume and best determined by onsite trials.

Packaging

MasterInject 1380 is available in units of 18kg.

Storage & Shelf Life

MasterInject 1380 has a shelf life of 12 months. Store out of direct sunlight, clear of the ground on pallets protected from rainfall.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.



MasterInject 1380

Structural concrete bonding process injection resin

Disclaimer

			MasterInject-1380-ANZ-V7-0623		
STATEMENT OF RESPONSIBILITY	The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.				
NOTE	Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.				
MB Solutions Australia Pty Ltd ABN 69 634 934 419 Unit 102, 2 Burbank Place Norwest NSW 2153		MB Solutions New Zealand Ltd 45C William Pickering Drive Albany, Auckland New Zealand	Emergency Advice: 1300 954 583 within Australia (24hr) 0800 001 607 within New Zealand		
Freecall: 1300 227 30 www.master-builders	0 s-solutions.com/en-au	Phone: +64 9 414 7233			