

MasterRoc MP 900S

Ultrafine cement for injection into rock and soil

Material Description

MasterRoc MP 900S is a well graded cement milled from pure Portland cement clinker with a small portion of mineral addition.

Blaine value of >900 m2/kg.

Due to its small particle size it penetrates very well into tight joints, fissures and pore spaces to provide a watertight grouted rock or soil mass.

Areas of Application

- Pre-injection in all underground structures
- Also possible for post injection
- Water ingress reduction
- Ground stabilization
- Contact injection

Characteristics & Benefits

- Excellent penetration into tight joints, fissures and pore spaces
- Durable
- Better working environment no hazardous components
- Economical solution
- Standard cement injection equipment can be used

Technical Data

Fineness (Blaine)	> 900 m²/kg
Particle size distribution:	
D ₉₅	$< 13.5 \mu\mathrm{m}$
D ₅₀	$<$ 4.8 μ m
D ₂₅	$< 2.4 \mu m$
D15	$< 1.6 \mu m$
D10	$< 1.2 \mu m$
D5	$<$ 0.8 μ m
D2	$<$ 0.5 μ m
DI	$<$ 0.4 μm

Setting Times

Injection grout properties indicated below, relates to a mix containing 1.5% MasterGlenium SKY 8100 of cement weight:

Water/Cement ratio 1:1

Initial set: 6hrs (AS 2350.4)
Final set: 10hrs (AS 2350.4)
Mud balance 1.40 - 1.43 kg/l
Flow cone <45 s
Bleeding maximum <3%

Mixing

- Fill the mixer with water
- Add Master Builders Solutions recommended water reducing admixture
- Add cement and mix for 2 minutes
- Transfer to agitator

It is very important to use an efficient mixer. Colloidal mixers give the best result. Minimum rpm for colloidal mixers is 1500. Paddle mixers are not recommended.

NB: Do not over mix. Mixing longer than recommended may cause the grout temperature to increase and set in the pump and hoses.

Application

MasterRoc MP 900S should always be used with a Master Builders Solutions recommended water reducing admixture (1.0 - 2.0 % of cement weight). The w/c ratio (by weight) should normally be between 0.6 and 1.0.

Pot Life

The mix should be kept under constant agitation prior to injection. Do not keep grout in agitator longer than $30-40\,$ minutes.



MasterRoc MP 900S

Ultrafine cement for injection into rock and soil

Injection

High-pressure piston pumps are normally used to pump the suspension into the rock. The grout should be injected within 30 - 40 minutes after mixing to ensure that it keeps penetrating into the fissures. Longer open times can be achieved by using MasterRoc HCA 20 stabilizer hydration control admixture.

Packaging

MasterRoc MP 900S is supplied in 20 kg paper bags and 1000 kg bags. For big jobs bulk tankers is a possible option.

Storage & Shelf Life

MasterRoc MP 900S has a shelf life of six months when stored in original closed bags in ventilated dry areas.

Precautions

For the full health and safety hazard information and how to safely handle and use this product, make sure that you obtain a copy of the Safety Data Sheet (SDS) from our office or website.

Disclaimer

MasterRoc-MP900S-ANZ-V4-0723

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this MB Solutions Australia Pty Ltd publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use and for ensuring that the application and use of the product is in accordance with the manufacturer's guidelines and recommendations.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by MB Solutions Australia Pty Ltd either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not MB Solutions Australia Pty Ltd, are responsible for carrying out procedures appropriate to a specific application.

MB Solutions Australia Pty Ltd ABN 69 634 934 419 II Stanton Road Seven Hills NSW 2147 MB Solutions New Zealand Ltd 45C William Pickering Drive Albany, Auckland New Zealand Emergency Advice:

Freecall: 1300 227 300

Phone: +64 9 4l4 7233

1300 954 583 within Australia (24hr) 0800 001 607 within New Zealand

www.master-builders-solutions.com/en-au