

MasterRheobuild[®] 1100 D

A high range water reducing superplasticising admixture for the production of rheoplastic concrete

DESCRIPTION

The basic components of **MasterRheobuild 1100 D** are synthetic polymers which allow mixing water to be reduced considerably and concrete strength to be enhanced significantly, particularly at early ages. **MasterRheobuild 1100 D** is a chloride free product.

PRIMARY USES

- Production of rheoplastic self-compacting concrete
- Pre-cast concrete
- Low water/cement ratio concrete.
- For concrete to be placed in complicated formwork or with congested reinforcement.

ADVANTAGES

MasterRheobuild 1100 D allows the production of very flowable concrete, with a low water / cement ratio. Table 1 shows some typical examples of reductions in w/c ratio. Concrete with **MasterRheobuild 1100 D** shows strengths higher than concrete without admixture having the same workability. The increase in strength, especially evident at early ages remains at later ages, both in air cured and steam cured processes. Initial and final sets do not change significantly with respect to concrete without admixture. Therefore, whenever longer transport and finishing times are needed, the use of retarding superplasticisers, such as **MasterRheobuild 850**, is recommended.

Due to the reduction in the water / cement ratio, all other properties of hardened concrete improve significantly, namely, lowered permeability, shrinkage and creep, increased workability and modulus of elasticity.

For more detailed information on the influence of superplasticisers on hardened concrete properties, consult your local Master Builders Solutions representative.

COMPATABILITY

MasterRheobuild 1100 D is compatible with all cements and admixtures meeting ASTM standards.

The use of **MasterRheobuild 1100 D** and **MasterAir 111** air-entraining agent is recommended whenever concrete is required to withstand freeze / thaw cycling.

PACKAGING

MasterRheobuild 1100 D is available in 1000 ltr. bulk

TYPICAL PROPERTIES

Colour:	Brown free-flowing liquid
Specific gravity:	1.12 at 24°C
Air-entrainment:	Maximum 1%
Chloride content:	Nil to BS 5075
Nitrate content:	Nil
Freezing point:	0°C can be reconstituted if stirred after thawing

STANDARDS

ASTM C-494 Types A and F
 BS 5075 Part 1 & 3.

DOSAGE

MasterRheobuild 1100 D is normally dispensed at a depending on the desired plasticising or water-reducing effect, at a rate of 0.3-2.5% cwt. Other dosages may be used, depending on the materials and conditions.

DIRECTIONS FOR USE

MasterRheobuild 1100 D should be added to the mix with the gauging water. No extension to the mixing time is necessary. Never add **MasterRheobuild 1100 D** to dry cement.

Alternatively, when using **MasterRheobuild 1100 D** to produce flowing concrete at site using ready mix trucks, it can be added to the concrete via the feed hopper at the rear of the truck. Mix before discharge for 3 minutes at 10rpm to produce a fully homogenous mix.

MasterRheobuild® 1100 D

When using **MasterRheobuild 1100 D** to obtain very high early strengths, advantage must be taken of its water reducing properties.

EFFECTS OF OVER DOSAGE

A severe over-dosage of **MasterRheobuild 1100 D** will result in the following:

- Retardation of initial and final set.
- Slight increase in air entrainment.
- Increase in workability.

DISPENSING

MasterRheobuild 1100 D is introduced into the mixer together with mixing water. The plasticising effect or water reduction is higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of **MasterRheobuild 1100 D** to dry aggregate or cement is not recommended.

STORAGE

Store under cover, out of direct sunlight and protect from extremes of temperature. Shelf life is at least 2 years when stored as above. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult Master Builders Solutions 's Technical Services Department.

SAFETY PRECAUTIONS

MasterRheobuild 1100 D contains no hazardous substances requiring labelling. For further information refer to the material safety data sheet.

NOTE

Field service, where provided, does not constitute Supervisory responsibility. For additional information contact your local Master Builders Solutions representative.

Master Builders Solutions reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products manufactured by Master Builders Solutions Egypt, or imported from Master Builders Solutions affiliate companies world-wide, are manufactured to procedures certified to conform to the quality, environment, health & safety management systems described in the ISO 9001:2015, ISO 14001:2015 & OHSAS 18001:2007 standards.

* Properties listed are based on laboratory-controlled tests.

® Registered trademark of a MBCC Group member in many countries of the world

