

MasterRoc[®] MP 350

One component water sealing injection resin for cracks and fissures in concrete and rock

DESCRIPTION

MasterRoc MP 350 is a single component hydrophilic polyurethane based injection resin which forms a permanent, impermeable and flexible sealing material on contact with water.

FIELDS OF APPLICATION

- Permanent crack sealing of underground structures
- Sealing of minor water ingress
- Upgrading of temporary water sealing to permanent solution
- For use with **MasterSeal 909** injection hoses

FEATURES AND BENEFITS

- Permanent sealing effect.
- Forms a closed cellular material giving an impermeable, high resilience seal against water ingress.
- Reacts in moist and wet surroundings.
- Good bonding to wet surfaces.
- Foams upon contact with water.
- Penetration of fissures smaller than 0.05 mm.

MasterRoc MP 350 can be injected as a simple resin, but also has a faster reaction option for flowing water by adding a small quantity of the **MasterRoc MP 350** Accelerator.

PACKAGING

Injection resin:

MasterRoc MP 350: 25 kg cans

Optional accelerator:

MasterRoc MP 350 Accelerator: 2.5 kg cans

TECHNICAL DATA*

MasterRoc MP 350

Density, 20°C	1.15 g/cm ³
Viscosity, 23°C	250 mPa.s
Color	Colorless
to yellowish	
Application temperature	+ 5°C to 40°C

APPLICATION PROCEDURE

Wet/flowing water conditions:

1. If required, add **MasterRoc MP 350** Accelerator to **MasterRoc MP 350** (up to 10%, depending on the required reaction time) and mix quickly and thoroughly.
2. Inject this mixture through a single component injection pump. The moisture / water from the ground or structure will cause the foaming and curing reaction.

Dry conditions:

1. For injection purposes, flush holes with water to thoroughly wet the injection area.
2. Inject **MasterRoc MP 350** through a single component injection pump.
3. If a faster reaction is required, add the optional **MasterRoc MP 350** Accelerator as described above.

MasterRoc[®] MP 350

REACTION TIME

The reaction time depends on the temperature of the product and the ground. As indicated in Table 1, the reaction times at different temperatures have been measured in the laboratory. Site trials should therefore be performed in advance. gel time, the temperature will have a big influence. Site tests are recommended.

Table 1: Reaction time with 10% **MasterRoc MP 350** Accelerator + 10% water

Initial Temperature °C	5	10	15	20
Start of foaming (sec)	98	63	41	30
End of foaming (sec)	145	128	109	88
Foam factor	6	7	8	8

CLEANING OF INJECTION EQUIPMENT

For short breaks in the injection procedure, pump Part A through the in-line static mixer nozzle. After finishing the injection, pump an appropriate agent or oil which does not contain water through the pump and injection lines.

STORAGE

MasterRoc MP 350 must be stored in airtight containers in a cool, dry place. If stored in tightly closed original containers under the above mentioned conditions it has a shelf life of 12 months. The product must be prevented from freezing.

SAFETY PRECAUTIONS

MasterRoc MP 350 is not hazardous. However, follow standard safety procedures when handling the product and wear gloves and face / eye protection. Avoid eye and skin contact. If skin contact occurs, wash with plenty of water and soap. In case of eye contact rinse with plenty of water and seek medical advice. For further information refer to Material Safety Data Sheet.

Uncured products should be prevented from entering local drainage systems and water courses. Spillage must be collected using absorbent materials such as sawdust and sand, and disposed of in accordance with local regulations.

* Properties listed are based on laboratory controlled tests.

® Registered trademark of a MBCC Group member in many countries of the world

Master_Builders_Solutions_CC-UAE/Roc_MP350/v2/07_14

STATEMENT OF RESPONSIBILITY

information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

The technical

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

Master Builders Solutions Construction Chemicals UAE LLC

P.O. Box 37127, Dubai, UAE

Tel: +971 4 8090800 Fax: +971 4 8851002

www.master-builders-solutions.ae

