

Ucrete UD200

Heavy duty polyurethane screed

DESCRIPTION

Ucrete UD200 is a unique HD Polyurethane resin floor with exceptional resistance to aggressive chemicals, heavy impact and temperatures up to 150°C.

Ucrete UD200 provides a lightly textured protective floor finish suitable for applications in wet and dry process environments. It is dense and impervious, providing the ideal floor finish for applications in the food and beverage, pharmaceutical and chemical industries and wherever a robust, long lived floor is required.

Ucrete Industrial Flooring has been widely used throughout industry for more than 40 years, many of the older floors are still in service. A detailed project reference list is available upon request

PERFORMANCE DATA

AIR QUALITY

Ucrete has been awarded the Indoor Air Comfort Gold Label following extensive VOC emission chamber testing and auditing of quality management and production control procedures.

This demonstrates that Ucrete is an extremely clean product without any volatile compounds that might taint foodstuff or affect the well-being of personnel.

All Ucrete grades give very low emissions and conform to all the emissions requirements for indoor flooring systems in Europe including AgBB in Germany, Afsset in France, where they are rated A+ for VOC emissions (the cleanest rating), and M1 in Finland.

For further information please contact your local BASF representative

NON TAINTING

Ucrete UD200 is non-solvented and non tainting from the end of mixing, as tested by the Campden Technology Ltd.

RAPID INSTALLATION

Specifications are available that enable Ucrete UD200 and primer to be installed and cured within a 12 hour application window. Being non tainting also, this makes it ideally suited for rapid refurbishment in the food industry.

TEMPERATURE RESISTANCE

The Ucrete UD200 resins do not start to soften until temperatures above 130°C are exceeded. Specifications are available that are fully serviceable up to 130°C and resistant to occasional spillage up to 150°C.

Correctly installed, Ucrete UD200 can withstand regular and routine discharges of boiling water, hot oils and fats.

CHEMICAL RESISTANCE

Ucrete UD200 offers exceptional resistance to a wide range of chemical aggressors. For example Ucrete is resistant to the following commonly encountered chemicals:

Acetic Acid, 50%: As spirit vinegar widely used in the food industry, indicative of resistance to vinegar, sauces, etc.

Concentrated Lactic Acid @ 60°C: Indicative of resistance to milk and dairy products.

Oleic Acid, 100% @ 60°C: Representative of the organic acids formed by oxidation of vegetable and animal fats widely encountered in the food industry.

Concentrated Citric Acid: As found in citrus fruits and representative of the wider range of fruit acids which can rapidly degrade other resin floors.

Methanol, 100%: Representative of alcohols and the wider range of solvents used in the pharmaceutical industry.

Ucrete UD200 is also resistant to a wide range of mineral oils, salts and inorganic acids, extensive chemical resistance tables are available upon request.

Note: some staining or discolouration may occur with some chemicals, depending upon the nature of the spillage and the standards of housekeeping employed.

IMPACT RESISTANCE

With high mechanical strengths and a low elastic modulus, Ucrete UD200 is very resilient and able to withstand severe impact loads. While no material is indestructible and surface chipping may occur, brittle modes of failure resulting in cracking and disbondment are unknown with Ucrete floors.

Ucrete UD200

Heavy duty polyurethane screed

SUBSTRATE MOISTURE TOLERANCE

Ucrete Industrial Flooring is extremely tolerant to residual substrate moisture and can be installed directly onto 7 day old concrete, or onto old good quality concretes with high moisture contents without the use of special primers, provided there is a functioning DPM within the structure.

This enables rapid construction programmes to be maintained and facilitates refurbishment work in wet process areas.

Epoxy surface DPMs should not be used as they soften under high temperature conditions and will lead to floor failure.

PERMEABILITY

Ucrete UD200 exhibits zero absorption when tested to CP.BM2/67/2.

CLEANING & HYGIENE

Ucrete flooring systems are accredited for use in facilities operating HACCP based food safety systems.

Ucrete UD200 is readily cleaned using industry standard cleaning chemicals and equipment.

Tests undertaken by Campden Technology Ltd on the removal of *Acinetobacter Calcoaceticus* and *Listeria Monocytogenes* concluded that the cleanability of Ucrete UD200 'compares well with the cleanability of food contact surfaces such as plastics and stainless steel'.

SLIP RESISTANCE

The Ucrete UD200 surface profiles have coefficient of friction as determined to EN 13036 Part 4 with 4S rubber on the wet floor as follows:

Ucrete UD200 40 – 45

The Ucrete UD200 surface profiles conform to DIN51130 as follows:

Ucrete UD200 R11 V -

Optimum slip resistance can only be maintained with regular cleaning.

COLOURS

Ucrete UD200 is available in eight standard colours:

Red	Yellow	Green	Orange
Grey	Cream	Blue	Green/Brown

Ucrete floor systems have been formulated to provide the very highest chemical and heat resistance. As a direct result some yellowing of the installed floor will occur in areas of direct UV exposure. This is most apparent in lighter colours.

SPECIFICATION

The floor finish shall be Ucrete UD200 from BASF plc, Construction Chemicals of 19 Broad Ground Road, Redditch, Worcestershire, B98 8YP installed at 6/9/12* mm in accordance with the manufacturers' instructions.

*(select as required)

*A 6mm Ucrete UD200 floor is fully resistant to liquid spillage and discharge up to 80°C and can be lightly steam cleaned. Suitable for freezer temperatures down to -25°C.

*A 9mm Ucrete UD200 floor is fully resistant to high temperature spillage and discharge up to 120°C and is fully steam cleanable. Suitable for freezer temperatures down to -40°C.

*A 12mm Ucrete UD200 floor is fully resistant to high temperature spillage and discharge up to 130°C and occasional spillage up to 150°C and is fully steam cleanable. Suitable for freezer temperatures down to -40°C.

In extreme thermal shock environments a well designed substrate of good quality concrete is essential.

SUBSTRATE QUALITY

Concrete substrates should be visibly dry and have a minimum tensile strength of 1.5 MPa.

Refer to the guide 'The Design & Preparation of Substrates for Ucrete Industrial Flooring'

All joints in the substrate concrete subject to movement should be reflected through the Ucrete floor and sealed with a suitable sealant

Ucrete UD200

Heavy duty polyurethane screed

COVERAGE

6mm: 13 – 15 kg/m²
9mm: 19 – 22 kg/m²
12mm: 24 kg/m²

CURING

Normally Ucrete UD200 floors can be put into service within 24 hours even at 8°C. Specifications are available that can be put back into service after 5 hours at 10°C.

CLEANING

Regular cleaning and maintenance will enhance the life and appearance of any floor. Ucrete UD200 is readily cleaned with industry standard cleaning chemicals and equipment. Please consult your local cleaning chemical or equipment supplier.

STORAGE

In covered warehouse conditions, above 5°C and below 30°C and out of direct sunlight. Materials must be raised off the floor and kept dry. Liquid components must be protected from frost.

DISPOSAL

Part 2 containers should be decontaminated with 5% sodium carbonate (washing soda) solution after use and disposed of as building waste in accordance with local regulations.

WARNINGS AND PRECAUTIONS

In its cured state Ucrete is physiologically non-hazardous.

For normal flooring applications Ucrete does not require the use of respiratory protective equipment during installation.

Operatives should consult the CoSHH risk assessment and their work instructions.

HANDLING AND TRANSPORT

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke or drink while working and wash hands when taking a break or when the job is completed.

Specific safety information referring the handling and transport of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

CONTACT DETAILS

BASF plc,
Construction Chemicals,
19 Broad Ground Road
Lakeside
Redditch
Worcestershire
B98 8YP

Tel: +44 (0) 1527 512255

Fax +44 (0) 1527 503576

www.master-builders-solutions.basf.co.uk


© BASF plc, Construction Chemicals

Ucrete UD200

Heavy duty polyurethane screed

Product Data	
Density	2090 kg/m ³
Compressive strength (EN13892-2)	52 - 57 MPa
Tensile strength (BS6319 Part 7)	6 MPa
Flexural strength (EN13892-2)	14 MPa
Compressive modulus (BS 6319:Part 6)	3250 MPa
Adhesive strength to concrete (EN13892-8)	concrete failure
Coefficient of thermal expansion (ASTM C531:Part 1.0F)	4 x 10 ⁻⁵ °C ⁻¹
Fire Testing (EN13501: Part 1)	B _{FL} – S ₁

Note:- Samples cured for 28 days at 20 °C

	
BASF Construction Chemicals 19 Broad Ground Road Lakeside, Redditch Great Britain B98 8YP	
04	
01040066	
EN 13813:2002	
Synthetic resin screed material	
Reaction to fire:	B _{FL} – S ₁
Release of corrosive substances:	NPD
Water permeability:	NPD
Mechanical resistance:	NPD
Wear resistance:	AR0,5
Bond strength:	B>2,0
Impact resistance:	IR>4
Sound insulation:	NPD
Sound absorption:	NPD
Thermal resistance:	NPD
Chemical resistance:	NPD
Electrical resistance:	NPD



Ucrete UD200

Heavy duty polyurethane screed

Ucrete® UD200 - BASF plc, Construction Chemicals, Version 2

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Solvent Based Products

Use in well ventilated areas; avoid inhaling. Suitable respiratory equipment may be needed, eg when spraying. Can cause skin, eye irritation. Wear protective eye shields and gloves during use. Do not smoke or allow sparks or naked lights when stored or in use.

Resin Products

Can cause irritation, dermatitis or allergic reaction. Use protective equipment particularly for skin and eyes. Use only in well ventilated areas.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"BASF plc, Construction Chemicals" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.