

MasterAir 760

Air entraining and plasticizing admixture for mortar

DESCRIPTION

MasterAir 760 is a ready-to-use powder mortar admixture, designed to entrain air, plasticise and extend workability.

FIELDS OF APPLICATION

MasterAir 760 is used in Dry Silo Mortar (DSM) to improve cohesiveness and workability retention, in both bricklaying and rendering applications.

MasterAir 760 aids resistance of mortar to frost attack in both wet and hardened state; also increases long-term durability of both cement/sand and cement/lime/sand mortar.

FEATURES AND BENEFITS

MasterAir 760 offers the following benefits for mortar:

- Increases open time of mortar
- Reduces bleed and segregation in the mix.
- Improves cohesiveness and bond strength.
- Improves frost resistance.
- Improves finish after pointing.
- Easy to use single admixture system

APPLICATION PROCEDURE

MasterAir 760 may be added directly into the mixer after the addition of sand or pre-mixed with the dry powder constituents.

DOSAGE

Dosage rates will vary depending upon climatic conditions and material constituents. Should the water demand of a mortar change this may require an adjustment in the dosage.

It is recommended that dosages between 200 to 800 grams per tonne of pre-blended powder constituents are used to obtain the correct air content (18 - 20 %) and open time of the mortar. The dosage rates given are for typical usages, they are not meant as absolute limits, test mixes should be carried out to determine optimum dosage.

To assist you in obtaining the optimum performance in mortars, please consult your Master Builders Solutions UK Ltd representative

PACKAGING

MasterAir 760 is Available in 20-kilo valve sacks or 500-kilo IBC sacks.

CONTACT DETAILS

Master Builders Solutions UK Ltd,
Swinton Hall Road,
Swinton,
Manchester,
M27 4EU

Tel: +44 (0) 161 727 6300

www.master-builders-solutions.com/en-gb

MasterAir 760

Air entraining and plasticizing admixture for mortar

Product Data	
Appearance:	White powder
Equivalent Sodium Content	3.2%
Sulphate Content	<0.1% (w/w) of admixture
Logistics	
Shelf life:	12 months if stored according to manufacturer's instructions in unopened container.
Storage conditions:	Store in original sealed containers and at temperatures between 5°C and 30°C. Store under cover, out of direct sunlight and protect from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.
Handling and transportation:	Refer to MasterAir 760 Safety Data Sheet
Disposal:	Refer to MasterAir 760 Safety Data Sheet



0086-CPR-469071



1073-CPR-7420

EN 934-3: T2

Declaration of Performance can be found at www.master-builders-solutions.com/en-gb

MasterAir 760 Master Builders Solutions UK Ltd, Version 4

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct.

However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.