

MasterGlenium SKY 1966

High range water reducing admixture for concrete - EN 934-2: T2

DESCRIPTION

MasterGlenium SKY 1966 is a high-performance super-plasticizer based on a unique blend of state of the art polymers, & is specially engineered for ready-mix concrete. Its particular configuration allows its delayed adsorption onto the cement particles and disperses them efficiently.

With MasterGlenium SKY 1966 it is now possible to obtain a high-quality concrete mix with extended workability without delayed setting characteristics, and superior concrete rheology. The unique polymer formulation enables true workability retention to be achieved across a broad spectrum of consistence classes (S4 to SF3). This is achieved without set retardation, or reduced 24-hour strength performance. Under normal conditions MasterGlenium SKY 1966 will remain within the target consistence class for 90 to 120 minutes.

TOTAL PERFORMANCE CONTROL

The Total Performance Control™ concept ensures that ready-mix producers, contractors and engineers get a concrete that is of the same high quality as originally specified; starting from production at the batching plant, to the delivery and application into place, and followed by its hardening process. Utilizing our well established advanced polymer technology, it provides a concrete mix with exceptional placing characteristics and optimised cement hydration for early strength development and high-quality concrete.

FIELDS OF APPLICATION

MasterGlenium SKY 1966 is especially beneficial for the production of high quality ready-mix concrete particularly when high water reductions are required in combination with a requirement for an extended period of workability, e.g. long-distance deliveries, deliveries with extended discharge times or in congested urban environments. MasterGlenium SKY 1966 is designed to exhibit workability retention for periods up to 2 hours. The formulation of MasterGlenium SKY 1966 has been particularly optimised for the more challenging retention issues that can be posed by the use of cementitious combinations such as, but not limited to, CIIIB.

FEATURES AND BENEFITS

MasterGlenium SKY 1966 offers the following benefits for:

The ready-mix producer:

- Production of a concrete with low water cement ratio that meets EN 206-1 without loss of workability.
- Single product for many application needs.
- Enhanced retention performance with cements containing either GGBS or PFA
- Confidence that the workability will be the same at the job site as it was when first produced.

The contractor / applicator:

- Easier placing and faster strength development.
- Improved concrete surfaces.
- Guarantee to place the same concrete as specified and ordered from ready-mix plant.
- More versatile concrete mix.
- Long pumping distances both horizontally & vertically

The engineer:

- Insurance that concrete meets original specification
- Confidence in the concrete's ability to be placed in areas of congested reinforcement.
- High quality concrete with better durability.

DOSAGE

MasterGlenium SKY 1966 is particularly suited for mixes where higher strengths/low water cement ratios are required without significant workability reduction over a 2-hour period.

Although MasterGlenium SKY 1966 works on its own, its formulation has been optimised to work in a two-component system in conjunction with MasterSure 1970, when retention periods of greater than 2 hours are required. The normal recommended dosage rate range of MasterGlenium SKY 1966 is:

- *By Volume* - 0.30 to 1.50 litres per 100 kg of cement (binder) content.
- *By Weight* - 0.33 to 1.64 kg per 100 kg of cement (binder) content.

MasterGlenium SKY 1966

High range water reducing admixture for concrete - EN 934-2: T2

The dosage rates given above are for typical usages, they are not meant as absolute limits, as other dosages outside of the stated range, may be utilised in special cases according to specific job conditions. If required consult our Technical Services Department for advice. Trial mixes should be carried out to ensure optimum dosage and effect. Where the concrete is to be machine finished by utilising power float or power trowelling methods, we recommend that you contact the Technical Services Department for dosage rate guidance.

MIXING

MasterGlenium SKY 1966 is a ready-to-use admixture to be added to the concrete as a separate component. Optimal results are obtained if MasterGlenium SKY 1966 is dispensed into the concrete mix after the addition of the first 80% of the mixing water, i.e. when all solids are wetted out. Avoid adding the admixture to the dry aggregates and cement.

COMPATIBILITY

MasterGlenium SKY 1966 can be used with all types of EN 197 Cements. For use with other special cements, contact our Technical Services Department.

MasterGlenium SKY 1966 should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing MasterGlenium SKY 1966 they must be dispensed separately.

In order to optimize special requirements, the use of the following complementary additives is suggested:

- MasterSure 1966 for controllable extended consistence retention performance.
- Viscosity modifying agent MasterMatrix to produce Smart Dynamic Concrete or Self Compacting Concrete.
- Air entraining agent MasterAir to improve frost/thaw resistance.

When such complimentary admixtures are required it is important that laboratory trials are performed, prior to any supply, to determine the respective dosages of any complimentary admixture, and the suitability, in the fresh and hardened state, of the resultant concrete. In these

circumstances, we recommend that you consult our Technical Services Department for further advice.

PACKAGING

MasterGlenium SKY 1966 is supplied in Bulk & 1000-litre IBC's.

CONTACT DETAILS

Master Builders Solutions UK Ltd,
Swinton Hall Road,
Swinton,
Manchester,
M27 4EU
Tel: +44 (0) 161 727 6300
www.master-builders-solutions.com/en-gb

MasterGlenium SKY 1966

High range water reducing admixture for concrete - EN 934-2: T2

Product Data	
Appearance:	Brown liquid
Specific gravity @ 20°C:	1.08 ± 0.02 g/cm ³
Solids content:	32.0 ± 1.5%
pH-value:	5.5 ± 1
Alkali content (%):	≤ 2.00 by mass
Chloride content (%):	≤ 0.10 by mass
Corrosion behaviour:	Contains only components according to BS EN 934-1:2008, Annex A.1
Air Content:	Fulfilled
Water reduction:	≥ 5% of Reference mix
Compressive strength - 7 day:	≥ 110% of Reference mix
Compressive strength - 28 day:	≥ 110% of Reference mix
Compressive strength:	Compressive strength:
Durability:	Durability:
Dangerous substances:	Dangerous substances:
Logistics	
Shelf life:	12 months if stored according to manufacturer's instructions in unopened container.
Storage conditions:	Store in original sealed containers and at temperatures between 5°C and 30°C. Store under cover, out of direct sunlight and protect from extremes of temperature. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging.
Handling and transportation:	Refer to MasterGlenium SKY 1966 Safety Data Sheet
Disposal:	Refer to MasterGlenium SKY 1966 Safety Data Sheet



0086-CPR-469071



1073-CPR-7420

EN 934-2 : T2

Declaration of Performance can be found at www.master-builders-solutions.com/en-gb

MasterGlenium SKY 1966

High range water reducing admixture for concrete - EN 934-2: T2

MasterGlenium SKY 1966, Master Builders Solutions UK Ltd, Version 3

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.