

MasterLife WP 588

Elastomeric watertight brushable or sprayable membrane

Material Description

This is an elastomeric watertight coating forming a brushable or sprayable membrane for concrete and masonry. MasterLife WP 588 comes as two-part, powder and liquid component. When the two components are mixed together to form MasterLife WP 588, it forms a brushable watertight slurry, which cures to a flexible elastomeric membrane. It is applied to a minimum 2 mm thickness in two coats by stiff brush, broom, or spray.

Areas of Application

- Water retaining structures which may be subject to movement
- As part of the basement waterproofing system, in areas sensitive to movement, vibration and settlement
- To protect concrete from water of low pH or soft quality, carbonation, and de-icing salts
- Suitable for internal and external use, against positive and negative water pressure
- As a resilient coating to protect concrete on bridge parapets, columns, piers, on land and in marine environments
- Waterproofing of new structures where movement is expected from drying shrinkage
- Once cured, a 2mm thick MasterLife WP 588 membrane will accommodate up to 0.5mm, or 1.5mm of movement when reinforced with FX Mesh.

Note: MasterLife WP 588 is not suitable for prolonged contact with hydrocarbons such as petrol, fuel oil, etc.

Features and Benefits

- Retains flexibility when submerged
- Good chemical resistance against soft water, domestic and sewage wastewater, and other liquids moderately aggressive to mineral substrates
- Resistant to occasional foot traffic
- 2mm of cured coating equivalent to 500mm of concrete cover
- Freeze/thaw resistant
- Water vapour permeable (contact Master Builders Solutions UK Limited if you require more specific advice)
- Non-solvented – safe to handle and use: environmentally friendly

Application Method

For tanking applications refer to the Basement Waterproofing Guide.

Substrate Quality

Substrates to be treated must be completely clean, structurally sound, and mechanically keyed. All surface coatings, defective renders, foreign matter, formwork treatments and other contaminants that may affect the bond adversely should be removed.

(a) Surface Preparation

Substrates should be prepared by abrasive blasting or high-pressure water treatment. Do not use scabbling or any other aggressive method.

All mortar joints to be flush-pointed, repair with MasterLife WP 590.

All wall/floor intersections to be prepared by cutting a 20mm by 20mm chase along the junctions and filling with MasterLife WP 590, finishing in an angle fillet to "round out" the junction.

Water infiltration through the substrate to be treated should be either diverted by drainage or concentrated at weepholes, which will be plugged with MasterLife WP 590 after the application of the final coat of MasterLife WP 588.

Basements in areas containing high levels of soil or ground water sulphates may require a pre-treatment render. Consult Master Builders Solutions UK Ltd for details.

(b) Mixing

Liquid content
10 litres of MasterLife WP 588 liquid per 25 kg bag of MasterLife WP 588 powder.

MasterLife WP 588

Elastomeric watertight brushable or sprayable membrane

Mechanical Mixing

Blend the powder into the mixing liquid. Use a suitable mixing paddle in a slow speed drill (400 - 600rpm). Mix until a lump-free, slightly viscous slurry is obtained. This should be achieved within 2 minutes. Do not over mix.

Allow the mixed material to stand for 10 minutes for full saturation to take place. If applying by spray add 0.4 litre of MasterLife WP 588 liquid. Re-mix for 10 - 20 seconds before use.

Mixed material must be used within 60 minutes from the start of mixing, or less under hot weather conditions.

Do not re-temper the mix.

Application Method

MasterLife WP 588 can be applied by *brush, broom, or spray. MasterLife WP 588 must not be applied by trowel.

* A suitable brush will be 6" (150mm) in width and have a short pile comprising stiff nylon bristles of 3" (80mm) in length. The first coat MUST be worked into the substrate with a stiff brush, while still wet, to ensure an intimate bond to the substrate, even when applied by spray.

Finishing and Cleaning

Tools, equipment, and spillages should be cleaned immediately with clean water.

Curing

Damp cure for 24 hours after which time the MasterLife WP 588 must be allowed to air dry.

In cold, humid, or unventilated areas it may be necessary to leave the application for a longer curing period or to introduce forced air movement. NEVER use dehumidifiers during curing periods.

Working Time

45 minutes in 20 °C ambient and substrate temperature.

Packaging

MasterLife WP 588 powder is available in 25kg bags.

MasterLife WP 588 liquid is supplied in 10ltr plastic containers.

Coverage

Approximately 2 l m² per pack at 1 mm thickness in one coat.

Apply 2 coats.

Coverage is influenced by the roughness of the substrate. On rough substrates the quantities required will increase significantly.

Storage

MasterLife WP 588 should be stored under cover, clear of the ground and stacked not more than 6 bags high. Protect the materials from all sources of moisture and frost.

Shelf Life

Rotate stock in order not to exceed the shelf life of 12 months.

Watchpoints

If MasterLife WP 588 is used to waterproof fish tanks, it should be washed down after curing is complete with salt water and rinsed with clean water. Repeat the rinsing until the required pH conditions are obtained. Failure to do this and to monitor the pH of the water until stable can lead to the death of fish.

Handling and Transport

Usual preventive measures for the handling of chemical products should be observed when using this product, for example do not eat, smoke, or drink while working and wash hands when taking a break or when the job is completed. Specific safety information referring the handling and transport

MasterLife WP 588

Elastomeric watertight brushable or sprayable membrane

of this product can be found in the Material Safety Data Sheet. For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

Disposal of product and its container should be carried out according to the local legislation in force. Responsibility for this lies with the final owner of the product.

Contact Details

Master Builders Solutions UK Ltd
Swinton Hall Road,
Swinton,
Manchester,
M27 4EU
Tel: +44 (0) 161 727 6300
www.master-builders-solutions.com/en-gb

MasterLife WP 588

Elastomeric watertight brushable or sprayable membrane

Product Data			
Property	Standard	Unit	Data
Density of mixed material	EN 1015-6	kg/m ³	approx. 1680
Maximum particle size	-	mm	0.6
Mixing time	-	minutes	Approx. 2
Maturing time	-	minutes	10 Maximum
Workability time	-	minutes	Within 60 (+20°C)
Total application thickness	-	mm	2
Application temperature (substrate and material)	-	°C	from +5 to +30
Water vapour permeability	-	μ	985
Resistance to chloride ion penetration	-	%	0.001
Tensile strength 28 days	-	MPa	0.64
Adhesive strength 28 days	-	Mpa	1.0
Freeze/thaw resistance	ISO/DIS 4846.2)	-	No scaling after 50 cycles
Water absorption	(Astm 642C)	%	1.5
Positive side waterproofing	-	bar	1.5
Negative side waterproofing	-	bar	1.0
Static crack bridging:	EN 1062-7	mm	0.5 (+20°C)
			Reinforced with mesh 1.5 (20°C)
CO ₂ permeability	-	μ	100,000
Equivalent concrete cover to 2mm of coating	-	mm	500 (P35 grade concrete)

MasterLife WP 588

Elastomeric watertight brushable or sprayable membrane

Disclaimer

MasterLife WP 588, Master Builders Solutions UK Ltd, Version I

Health and Safety

*For full information on Health and Safety matters regarding this product the relevant Health and Safety Data Sheet should be consulted.

The following general comments apply to all products.

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs, (which may also be tainted with vapour until the product is fully cured and dried). Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Keep away from children and animals. Reseal containers after use.

Spillage

Chemical products can cause damage; clean spillage immediately.

DISCLAIMER

"Master Builders Solutions UK Ltd" (the Company) endeavours to ensure that advice and information given in Product Data Sheets, Method Statements and Material Safety Data Sheets (all known as Product Literature) is accurate and correct. However, the Company has no control over the selection of its products for particular applications. It is important that any prospective customer, user or specifier, satisfies him/her-self that the product is suitable for the specific application. In this process, due regard should be taken of the nature and composition of the background/base and the ambient conditions both at the time of laying/applying/installing the material and when the completed work is to be brought into use.

Accordingly, no liability will be accepted by the Company for the selection, by others, of a product, which is inappropriate to a particular application.

Products are sold subject to the Company's standard conditions of sale and all customers, users and specifiers, should ensure that they examine the Company's latest Product Literature.