









MasterTop 1324

Universal polyurethane system, smooth, matt, low emission

Application: Static crack bridging, indoor system, bearing medium to heavy loads.

For production areas, warehouses and technology rooms etc.

		consumption ca.:	
	Primer	MasterTop P 604 or P 617 (or P 615 without sand broadcasting) EP,2 component, non-solvented (total solid)	0,3-0,5 kg/m ²
	Sand broadcast	Oven dried silica sand, size 0,3-0,8 mm, uniformly applied, not in excess	0,8-1,0 kg/m ²
	Optional/ Scratch primer	MasterTop P 604 or P 617 (or P 615 without sand broadcasting) Filled 1 : 0,5 up to 1:1 with oven dried silica sand, size 0,1-0,3 mm	0,6-1,0 kg/m ^{2*}
	Sand broadcast	oven dried silica sand, size 0,3-0,8mm	2,0-3,0 kg/m ²
	Optional**/ Pore sealer	MasterTop BC 375N pigmented, PU, 2-component, non-solvented, 1 : 0,3 filled with oven Dried silica sand, size 0,1-0,3 mm	0,9-1,2 kg/m ^{2*}
	Body coat	MasterTop BC 375N pigmented, PU, 2-component, non-solvented, 1 : 0,3 filled with oven dried silica sand, size 0,1-0,3 mm	2,0-2,4 kg/m ^{2*}
	Top coat	MasterTop TC 442W pigmented pigmented, PUR, 2 component, water-based, UV resistant, silk-mat	0,08-0,10 kg/m ²
	Optional***/ Top coat if decorative chips are broadcasted	MasterTop TC 442W clear, PUR, 2 component, water-based, UV resistant, silk-mat	0,10-0,15 kg/m ²
	Total thickness of the system	ca. 2,0-3,0 mm	



MasterTop 1324

Universal polyurethane system, smooth, matt, low emission

Remark:	Consumptions are indicative and may be higher, depending on substrate roughness, temperature and porosity, as well as waste produced during application.
* Consumption incl. filler	
** Pore sealer is required on sand broadcasted, porous and absorbent surfaces	
*** Clear top coats can not stop yellowing of the aromatic body coat. Aliphatic pigmented top coats are necessary	

The flooring system fulfills, as minimum requirements, the following properties and technical data determined by internal and external testing:

DIBt General technical approval **Z-156.605-685** according to DIN EN 13813:2003-1 for the utilization indoor in public areas with Health-related Evaluation Procedure for Volatile Organic Compounds Emissions (VOC and SVOC).

EN 13813	SR-B1,5-AR1-IR4-Bfl-s1
Emissions behavior	AgBB conform AFFSET conform A+ classification
Bending tensile strength	28 N/mm ² (after 7 days)
Compressive strength	51,5 N/mm ² (after 7 days)
Slip resistance	R 9 with top coat MasterTop TC 442W R 10 with MasterTop TC 442W (+ 4% glass beads) R 11 with MasterTop TC 442W (+ 4% Ballotini)
Taber abrasion	88 mg/1000 U (without top coat) < 50 mg/1000 R (with MasterTop TC 442W)
Crack bridging at 23 °C	Class A 3 according to DIN EN 1062-7 Requirement > 500 µm, result = 900 µm
Ease of decontamination	DIN 25 415, Part 1: Assessment: excellent
Fire behavior	Bfl-s1 (DIN EN 13501-1)

Resistance to blistering under the influence of moisture from the reverse side (with MasterTop P 615 and P 617)



MasterTop 1324

Universal polyurethane system, smooth, matt, low emission

CONTACT

Should you require any further information, please do not hesitate to contact your local sales consultant or take directly contact with us:

Master Builders Solutions Hong Kong Limited
Unit 2, 20/F, EW International Tower
120-124 Texaco Road, Tsuen Wan, N.T., Hong Kong

Tel: +852 2408 4400
Fax: +852 2408 4401

Mitglied der



Disclaimer:

In view of widely varying site conditions and fields of application of our products, this technical data sheet is meant to provide general application guidelines only. This information is based on our present knowledge and experience. The customer is not released from the obligation to conduct careful testing of suitability and possible application for the intended use. The customer is obliged to contact the technical help-line for fields of application not expressly stated in the technical data sheet under "Fields of Application". Use of the product beyond the fields of application as stated in the technical data sheet without previous consultation with Master Builders Solutions and possible resulting damages are in the sole responsibility of the customer.

All descriptions, drawings, photographs, data, ratios, weights i.e. stated herein can be changed without advance notice and do not represent the condition of the product as stipulated by contract. It is the sole responsibility of the recipient of our products to observe possible proprietary rights as well as existing laws and provisions. The reference of trade names of other companies is no recommendation and does not exclude the use of products of similar type. Our information only describes the quality of our products and services and is no warranty. Liability is accepted for incomplete or incorrect particulars in our data sheets only in the event of intent or gross negligence, without prejudice to claims under product liability laws.