

THIS METHOD STATEMENT COVERS THE SURFACE PREPARATION, MIXING & APPLICATION OF **Ucrete HF60RT (6mm)**

## **METHOD STATEMENT: Ucrete HF60RT (6mm)**

### **1. PREPARATION:**

- 1.1. At the time of installation of the **Ucrete HF60RT** the substrate concrete should have a minimum tensile strength of >1.5 MPa (tested / confirmed on site), be more than 7 days old and the surface should be dry.
- 1.2. Surface laitance must be removed by mechanical action using suitable equipment including Captive Shot Blasting equipment, Concrete Planers and Scarifiers. Diamond grinding can be used for edge work etc. with limited access.
- 1.3. Anchor / Termination grooves (see below) to be cut into the substrate where not already present.

### **2. DETAILING:**

- 2.1. Anchor / Termination grooves must be present in the surface of the concrete within 75 mm of all 'free edges' and are typically cut into the surface with a suitable concrete groove cutter (double bladed – Hilti). 'Free Edges' includes all joints, column bases, perimeter walls, drainage channels, door thresholds etc. **and every 4 m across the floor in both directions.**
- 2.2. Anchor Joints are also required wherever movement is expected including adjacent to stainless steel channels, machine bases, around columns and at any construction joint in the substrate.
- 2.3. **NB: Anchor / Termination grooves are nominally square in section for the Ucrete Systems and should be twice the thickness of the floor in both width and depth.**  
**6 mm thick Ucrete HF60RT – 12 mm x 12 mm**
- 2.4. Anchor / Termination grooves should be included on both sides of all day joints within the substrate in preparation for a joint, should movement subsequently occur.
- 2.5. At soft joints subject to traffic and at channels, the chases should abut the joint, to provide extra protection to the arris against impact and to prevent the ingress of liquids under the floor in the event of sealant failure.

**NB: Refer to Master Builders Solutions detailed Sketches for Anchor and Termination Grooves.**

### **3. PRIOR TO INSTALLATION:**

#### **3.1. Storage (Temperatures)**

Materials should be stored under cover, out of direct sunlight and preferably in a temperature-controlled environment for at least 48 hours prior to usage. **PTC** must be raised off the floor and kept dry. **PTA** and **PTB** and the **Sachet of Liquid Polykit Pigment** must be protected from temperature extremes.

**NB: Required Storage temperature: 15°C to 22°C.**

The substrate concrete should be installed to the tolerances required of the finished floor. Any repairs to the substrate or correction of levels etc. should be done in good time prior to the installation of the **Ucrete HF60RT**.

#### 4. INSTALLATION OF THE UCURETE HF60RT:

4.1. **Ideal application temperatures are 12°C to 25°C (Max). Relative Humidity levels affect the curing rate of the Ucrete system and ideally should be above 50% during application.**

4.2. The mixed **Ucrete HF60RT** should be within **15°C to 20°C (Max)** range during installation. Once laid **Ucrete** will cure very effectively even at low temperatures.

Applications should not proceed if the temperature is expected to be less than 3°C below the dew point at any time during the operation.

#### 4.3. Summary of Storage, Mixing and Application Temperatures.

Item	Temperature
Material Storage Area	15°C to 22°C
Mixed Material	15°C to 20°C
Application area (Ambient)	5°C to 25°C
Substrate Surface	12°C to 25°C

**NB: UCURETE** should not be applied in direct sunlight or to very hot substrate surfaces.

#### 5. UCURETE PRIMER FS – (Scratch Coat 1 mm)

**(Fast Setting - Heavy Duty Fast Slurry Primer)**

**UCURETE PRIMER FS** should not be applied on to:

Damp substrates - Concrete and other cementitious substrates must be visibly dry.

Weak substrates - the average pull-off strength shall be >1.5 N/mm<sup>2</sup>.

Application to substrates of lower strength may affect the long-term performance of the applied flooring. This is particularly relevant in areas subject to heavy use be it thermal or mechanical.

#### 5.1. Mixing

a) Pour the contents of the **PTA (Red Cap – 2.83 kg)** and the **PTB (Blue Cap – 2.86 kg)** into a 20 L polyethylene mixing pail and mix using a suitable slow speed hand held mixer with a **Collomix KR** type mixing head for 20 seconds.

b) Add the **PTC bag (7 kg)** and continue mixing for a further 2 minutes or until the mix becomes homogeneous. **DO NOT overmix.**

- c) The working life is approximately 10 minutes. Multiple units may be mixed, but **Do Not** mix more material than can be applied in 10 minutes.

## 5.2. Application of UCRETE PRIMER FS

The **UCRETE PRIMER FS** is applied by squeegee or steel trowel from:

**0.6 kg/m<sup>2</sup> (0.38 mm) – 1.6 kg/m<sup>2</sup> (1mm)**

**NB: Maximum (3 kg/m<sup>2</sup> can be applied - 1.85 mm)**

- 5.3. Above coverage rate will depend on substrate profile and does not include any wastage.
- 5.4. **Mixed material should be poured out immediately onto the floor otherwise it will Exotherm very quickly and set. Do NOT leave mixed material in the buckets**
- 5.5. Anchor grooves (12 x 12 mm) to be filled with **UCRETE PRIMER FS** and then lightly brushed out to remove excess material. They would then be filled with the subsequent **Ucrete HF60RT** system.
- 5.6. The subsequent over-coating / application can be carried out when the **UCRETE PRIMER FS is tack free** typically as follows.
- 5.2.1. 8 hours at 10 - 15°C
  - 5.2.2. 6 hours at 20°C
  - 5.2.3. 4 hours at 30°C

**The above timings are dependent upon both temperature AND humidity. If the humidity is <50% a delay in setting / curing of the UCRETE PRIMER FS can be expected and overlayment times would need to be extended.**

**The surface MUST be dry to the touch before overlaying. Premature application of the Ucrete HF60RT overlayment can lead to bubbles in the surface (out-gassing). Ideally the primer should be left overnight (12 hours).**

- 5.7. Ensure that **UCRETE PRIMER FS** has been correctly applied and cured. The use of **UCRETE PRIMER FS** is mandatory to ensure the best surface finish and to aid application by reducing resin absorption into the concrete.
- 5.8. **NB:** Should the primer coat be left for more than 48 hours; mechanical surface preparation will be required to produce a suitable surface for the application of the body coat. This will necessitate repriming.

## 6. APPLICATION OF UCRETE HF60RT (6 mm)

**ENSURE the room and materials to be used are ALL at the correct temperature (12° -25°C MAX).**

The length of the application bay should be such as to produce a strip of material along the whole length of the bay from a single or double mix to allow for efficient trowelling and maintaining a wet joint for finishing.

**Recommended maximum length of any application bay is as follows:**

Thickness	Bay Size Width (Max)		Bay Size Width (Max)
6 mm	4 – 5 m long (1 mix)		8 – 10 m long – (double mix)

**Ucrete HF60RT** consists of four components.

- 6.1. Mix the **Ucrete HF60RT** components **PTA (Yellow Cap) (2.52 kg)** and **PTB (Blue Cap) (2.86 kg)** and the **Sachet of Liquid Polykit Pigment (0.5 kg)** together for 1 minute with a slow speed drill (300 – 350 pm) and **Collomix KR** type mixing head or a forced action pan mixer to create a uniform dispersion.

Gradually add the **PTC aggregates (22.50 kg)** whilst mixing continues for **typically 3 – 4 minutes**. Only whole units are to be mixed. Nothing is to be added or left out. **DO NOT OVERMIX.**

The mixed material should be transferred into a clean bucket and taken to the application area. Do not mix more than 2 kits at a time. Transport and discharge the mixed material on to the substrate as quickly as possible.

- 6.2. Spread the mixed **Ucrete HF60RT** evenly over the substrate using a pin screed or surface notched scraper set to the correct thickness (5 mm) at the following coverage rate.

**(a) 5 mm: 10 – 11 kg/m<sup>2</sup>**

**NB: Above coverage rate will depend on substrate profile and does not include for any wastage.**

- 6.3. The use of a spiked roller in gentle long sweeps over the surface will provide a more even finish. Rolling is best conducted immediately after application by the pin screed. The spiked roller should only be rolled 100 mm into the previous mix.

Care should be taken not to roll back into material that is partially cured.

The roller should be passed over the surface a maximum of twice as excessive rolling will have a detrimental effect on slip resistance and surface finish.

- 6.4. **DO NOT Apply** when atmospheric condensation is occurring or likely to occur before full cure is attained, i.e., when the dew point is reached or when the ambient or substrate temperature is within 3°C of the dew point. Normally full cure is reached after 24 hours, but under very cold or very dry conditions this may be extended to 48 hours.

- 6.5. Expansion Joints in the **Ucrete HF60RT** are best produced by saw cutting the material with a double-bladed joint cutter after application and cure.

- 6.6. **MasterSeal CR 460** Joint Sealant to be applied as per **Master Builders Solutions Method Statement.**

## 7. POST INSTALLATION:

- 7.1. No Building Trades or traffic to be allowed on to the freshly laid **Ucrete HF60RT** for at least 16 hours at 15°C to 20°C, longer at lower temperatures.
- 7.2. It is normal for the installation of joints to take place and no other trades should have access until the sealant has cured sufficiently to resist damage.
- 7.3. If the floor is to be handed to the client in a pristine condition it must be protected from other trades. Full protection of the whole floor by temporary covers consisting of polyethylene sheeting overlaid with hardboard, or plywood depending on the trades and traffic to have access, with joints taped and fixed. Ensure the floor is completely tack free at the time of covering, typically after 24 hours at 15°C to 20°C.

### NOTE:

The above guide provides a summary of the installation of a **Ucrete HF60RT** floor and should be read in conjunction with our technical data sheets.

The **Ucrete** Applicator is a specialist in the installation of **Ucrete** floors and is to install the floor in accordance with our current guidelines and best site practice.

**UCRETE INDUSTRIAL FLOORING** is only available from:  
**Master Builders Solutions Construction Chemicals LLC, P O Box 37127, Dubai, U.A.E.**

---

### STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this Master Builders Solutions publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

---

### NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by Master Builders Solutions either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not Master Builders Solutions, are responsible for carrying out procedures appropriate to a specific application.

---