

MasterSeal® P 698

Single Component, Moisture Curing Polyurethane Based Primer

DESCRIPTION OF PRODUCT

MasterSeal® P 698 is a single component, moisture curing polyurethane primer. It contains solvents.

FIELDS OF APPLICATION

MasterSeal® P 698 is intended for use as a primer on bituminous substrates e.g. roofing felt under **MasterSeal®** spray applied and hand applied waterproofing membranes in roofing applications. The solvents used in **MasterSeal® P 698** have been selected to have a minimum effect on the bitumen.

FEATURES AND BENEFITS

- Excellent adhesion to bituminous substrates
- Solvents do not attack bitumen
- Quick to cure
- Low viscosity
- Easy to apply

APPLICATION PROCEDURE

Preparation of Substrate

The bitumen felt substrate must be clean and dry and free from oil, grease and loose material and any other substance which may impair adhesion. In addition the bitumen felt must be firmly bonded to the substrate. Any blisters must be cut open, dried out and re-bonded. The temperature of the substrate must be at least 3 K above the dew point.

APPLICATION METHOD

MasterSeal® P 698 is a single component material. Prior to application, the temperature of the material should be in the range of 15- 25°C. Pour the amount required from the original container into an application container and apply evenly by roller, brush or by spraying to the prepared substrate. **MasterSeal® P 698** is moisture curing and will foam if applied too thickly. It is, therefore, important to apply **MasterSeal® P 698** thinly and to avoid ponding. Apply uniformly and finish by back rolling. The

curing time of the material is influenced by the humidity and the ambient and substrate temperatures.

COVERAGE

The consumption of **MasterSeal® P 698** is 0.05-0.15 kg/m² depending on the condition and porosity of the substrate.

WATCH POINTS

- Avoid application under excessive heat or wind and/or when the ambient and/or substrate temperature is below +10°C or above +30°C.
- The materials to be used at the appropriate temperatures should be brought and stored in the application area 1-2 days prior to the application and enabled to adjust the ambient conditions.
- In extremely cold conditions, heaters should be used to increase the ambient and the workability of the product, the packages should be preconditioned to +20°C +25°C to become ready to use.
- Epoxy and polyurethane based floor coatings should be applied by specialists.
- The reaction and workability times of resin based systems depend on the ambient and substrate temperatures as well as the relative humidity. Under lower temperatures, the chemical reaction times are prolonged and this increases the pot life, coating interval and the working time. In addition to this, the consumption is increased as the viscosity increases. High temperatures ignite stronger chemical reactions and the above mentioned times decrease accordingly. For the material to be cured properly, the ambient and the substrate temperatures should not fall below the specified limits. After the application, the material should be protected from direct contact with water for 24 hours minimum. Within this period, a contact with water may cause a surface carbonation and/or tackiness; both of which will cause the coating to lose its characteristics. In such cases, the overall coating should be removed from the floor and renewed.
- Permissible relative humidity 40%-90%.

TECHNICAL DATA

MasterSeal® P 698	Polyurethane
Colour	Clear
Solids Content	43 %
Density	1,00 kg/liters
Viscosity	12 s
Recommended Application Temperature Range	8-30°C
Re-coating Interval/Ready for Traffic	Min. 1 h Max. 5 h

The above figures are valid for 23°C and intended as a guide only and should not be used as a basis for specifications.

MasterSeal® P 698

Single Component, Moisture Curing Polyurethane Based Primer

- **MasterSeal® P 698** as ready-to-use kits. No solvent etc should be added during application.
- The empty packs should be consolidated and disposed properly in order to prevent reusing of the packages.

CLEANING OF TOOLS

Used tools and equipment must be cleaned carefully with an appropriate solvent. Once cured **MasterSeal® P 698** can only be removed by mechanically.

PACKAGING

MasterSeal® P 698 supplied in 24 kg working packs

STORAGE

The product should be stored in its original package, in a cool and dry place protected from frost. For short term storage, maximum 3 palettes should be placed on top of each other and the shipment should be made on a 'first come, first go' basis. Palettes should not be placed on top of each other during long term storage.

SHELF LIFE

The shelf life is 12 months from the date of production under suitable storage conditions. Opened packages should be stored under suitable storage conditions and used within 1 week.

HEALTH AND SAFETY PRECAUTIONS

It is dangerous to approach the application sites with fire. Fresh air should be circulated in the storage and the application sites. During the application, a protective apparel, protective gloves, goggles and masks which comply with the Occupational Health and Safety Precautions Rules should be used. Due to the irritation effect of the uncured materials, the mixture should not come into contact with skin and eyes; in case of a contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children. For detailed information please consult the Material Safety Data Sheet.

DISCLAIMER

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is only responsible for the quality of the product. **Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is

implemented and nullifies the old ones.

CONTACT INFORMATION

Master Builders Solutions Yapı Kimyasalları Sanayi ve Ticaret Ltd. Şti.

Adres: Barbaros Mah. Begonya Sok.

Nidakule Kuzey Ataşehir, C Kapısı

No:3 E/5, 34746 Ataşehir İstanbul / Türkiye

Tel: 0216 217 88 00

Mail: mbs.tr@mbcc-group.com

Web: www.master-builders-solutions.com/tr-tr

© Registered trademark of a MBCC Group member in many countries of the world

MasterSeal® P 698 Technical Data Sheet -Revision Date: 12/2020