

MasterFinish® HC

A heat-resistant retarder for exposed-aggregate concrete

Description

MasterFinish HC is a chemical retarder specifically designed to produce uniform exposed-aggregate finishes on architectural precast concrete. Its excellent heat resistance makes it ideal to produce medium to deep etch exposed-aggregate concrete on panels that may reach 160 °F (71 °C) while curing.

Applications

Recommended for use in:

- Architectural precast/prestressed concrete
- Cast stone
- Steam curing, heated beds, hot concrete temperatures up to 160 °F (71 °C) (Lilac, Pink, Tan and Brown only)

Location

- Horizontal

Substrate

Applied to forms previously treated with MasterFinish QD 200 transfer agent.

- Steel forms
- Fiberglass forms
- Concrete forms
- Wood forms

Features

- High heat resistance
- Controlled penetration delays the set of the surface only
- Wide range of etches available, including light etches
- Color-coded
- Can accommodate high-pressure water washing

Benefits

- Allows for year-round casting
- Consistent water-washed, exposed aggregate surfaces
- Variety of exposed aggregate appearances
- Easy identification
- Ease and speed of production
- Saves time and labor when used as an alternative to sand blasting

Color

The material in every container of MasterFinish HC retarder is color-coded to show specific degrees of penetration. Each container bears the name of the color on the label.

Color Coding Information

Color (Code)	Depth of Etch	Aggregate Size* in. (mm)
Blue (18)	Light sandblast/acid etch	Less than 1/8 (3)
Gold (28)	Extra Light	1/8 – 1/4 (3 - 6)
Lilac (38)	Light	1/4 – 3/8 (6 -10)
Pink (48)	Medium Light	3/8 – 1/2 (10 -13)
Tan (58)	Medium	1/2 – 5/8 (13 - 16)
Brown (68)	Medium Deep	5/8 – 3/4 (16 - 19)

*Recommended aggregate size

Guidelines for Use

Yield: 150 - 200 ft²/gal (3.7 – 4.9 m²/L)

Surface Preparation: Forms must be clean, dry and non-porous. Seal porous forms of wood or concrete with MasterFinish PT 100 protective coating, specially formulated for use under retarders.

Mixing: Mixing this product increases the generation of flammable vapors. Mix product in an adequately ventilated area to ensure safe handling during this process. Stir the retarder well before using. Use a mechanical drill and Jiffy-type mixer (being sure to scrape the sides and bottom of the container) or pour back and forth between two containers to ensure that any settled materials will be thoroughly dispersed.

Application

1. A form release agent should be applied to all surfaces not receiving a retarder.
2. To eliminate cleaning of the form, apply MasterFinish QD 200 transfer agent to the form prior to applying the retarder.
3. Apply MasterFinish HC retarder in a thin uniform coat by spray, brush or roller at a rate of 150 - 200 ft²/gal (3.7 - 4.9 m²/L) (8 mils (0.2 mm) on wet film thickness gauge). This coverage should be achieved by applying two light coats with a short (3/8 in. (10 mm)) nap roller. Allow the first coat to dry for 10-20 minutes or until dry to touch before applying second coat.
4. The second coat should be applied perpendicular to the first coat with light roller pressure (a coating that is too thick is undesirable).
5. After the second coat is dry (approximately 10-20 minutes), the concrete or face mix may be placed.
6. If the placing of concrete is delayed for an unusual length of time, protect the retarder surface from rain or water.
7. When the element is lifted or the forms are removed, the retarded surface concrete is easily removed by sandblasting, high pressure waterwashing or dry-brushing. The retarder film will remain on the mold if MasterFinish QD 200 transfer agent was not used.

Clean Up: Clean all tools and equipment with a lacquer thinner. Clean hands and skin with soap or industrial hand cleaner, not solvents.

For Best Performance

- Etches lighter than exposure of the tips of the coarse aggregate may be difficult to control due to changing conditions in day-to-day production. Consult your local sales representative prior to beginning jobs of this nature.
- Surfaces coated with MasterFinish HC retarder must be protected from water (rain, condensation, etc).
- Maintain consistent production schedules (stripping, washing, etc).
- Recommended maximum concrete temperature is 110 °F (43 °C) for Blue, 120 °F (49 °C) for Gold, and 160 °F (71 °C) for Lilac, Pink, Tan and Brown.
- Do not use MasterFinish HC retarder on styrofoam.
- Make certain the most current versions of product data sheet and safety data sheet are being used; call your local sales representative to verify the most current versions.

Mock Up

- Skill and practice are necessary to produce any high quality architectural finish. Samples and test mock-ups duplicating actual production conditions are essential to obtain a representative finish for approval prior to commencing production.
- Some important variables that should be controlled as close to actual cast conditions include: retarder coverage rate and method of application, mixture proportions and slump, admixtures, temperature of plastic and cured concrete, vibration, thickness of the element, length of time in form and method of cleaning.

Storage and Handling

Storage Temperature: Store in an unopened container in a cool, clean, dry area between 40 and 90 °F (4 and 32 °C). Keep containers tightly sealed after opening to maintain shelf life freshness. Protect from freezing.

Shelf Life: 2 years when properly stored.

In case of spillage, clean and dispose of in accordance with local, state and federal applicable regulations.

Packaging

5 gal (18.9 L) steel pails

VOC Content

570 - 676 g/L or 4.76 – 5.64 lb/gal, less water and exempt solvents.

Related Documents

Safety Data Sheets: MasterFinish HC retarder

Additional Information

For suggested specification information or for additional product data on MasterFinish HC retarder, contact your local sales representative.

The Admixture Systems business of BASF's Construction Chemicals division is the leading provider of solutions that improve placement, pumping, finishing, appearance and performance characteristics of specialty concrete used in the ready-mixed, precast, manufactured concrete products, underground construction and paving markets. For over 100 years we have offered reliable products and innovative technologies, and through the Master Builders Solutions brand, we are connected globally with experts from many fields to provide sustainable solutions for the construction industry.

Limited Warranty Notice

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.