



MasterFlow 648


High Strength, High Flow Epoxy Grout

MasterFlow 648 is the premier epoxy resin-based precision grout with carefully balanced physical properties used to secure critical equipment for proper alignment and transmission of static and dynamic loads.

Features:

- High Compressive Strength and Effective Bearing Area
- Excellent resistance to
 - Vibration and rotational torque
 - Creep
 - Chemical attack
 - Elevated service temperatures
- Formulated for easy installation
 - Excellent flow characteristics
 - Suitable for pouring or pumping
 - Low dust generation
 - Soap and water cleanup

MasterFlow 648 is available in all regions of the world, supported by trained BASF Construction Chemicals sales and technical personnel on every continent.



Please do not hesitate to contact us for more specific information!

www.masterflow-648.basf.com ■ 1-800-433-9517

Select technical data

Compressive Strength, ASTM C 579, Method B Ultimate Compressive Strength, psi (MPa)


Fill Ratio	7 Day Ambient	Post Cured*
Four Bag Mix	14,500 (100)	16,000 (110)
Three Bag Mix	14,000 (96)	15,000 (103)

* Cured 24 hours at room temperature, post cured 16 hours at 140°F, and conditioned 24 hours at test temperature.

Cure Rate/Compressive Strength, psi (MPa), when cured at: (four bag mix)

Time	50°F (10°C)	73°F (23°C)	95°F (35°C)
16 hours	–	7,500 (52)	8,500 (59)
1 Day	1,400 (10)	9,000 (62)	13,500 (93)
2 Days	9,000 (62)	12,500 (86)	14,000 (96)
3 Days	12,000 (83)	13,500 (93)	14,500 (100)
4 Days	13,500 (93)	14,500 (100)	15,000 (103)

Peak Exotherm



Flow Times and Bearing Area, ASTM C1339 (four bag mix)

Depth of pour	Back of Box	Full Plate Contact	Bearing Area
1" Clearance	11 Minutes	13 Minutes	High (>85 %)
2" Clearance	4 Minutes 50 Seconds	5 Minutes	High (>85 %)

Coefficient of Thermal Expansion, ASTM C 531 73–210°F (23–99°C), in/in/° F (cm/cm/°C)

Four Bag Mix	1.8×10^{-5} (3.22×10^{-5})
Three Bag Mix	2.0×10^{-5} (3.6×10^{-5})

Shrinkage, ASTM C 531, unrestrained; linear, %

Four Bag Mix	0.014
Three Bag Mix	0.031

Creep, ASTM C 1181, in/in 600 psi, 140°F (4.1 MPa, 60°C) @ 28 Days

Four Bag Mix	4.2×10^{-3}
Three Bag Mix	4.9×10^{-3}



BASF Corporation
Construction Systems
889 Valley Park Drive
Shakopee, MN 55379 USA

Customer Service 1(800) 433-9517
Technical Service 1(800) 243-6739
master-builders-solutions.basf.us



UL
Listed for use in
concrete applications
UL 1000

® = Registered trademark of the BASF-Group in many countries.
© 2016 BASF Corporation 1030762 rev 09/16

LIMITED WARRANTY NOTICE: BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.