

# MasterTop<sup>®</sup> 1215 AHS

Epoxy and polyurethane flooring system for aircraft hangars

FORMERLY AIRCRAFT HANGAR FLOOR SYSTEM

## YIELD

Primer: 200 ft<sup>2</sup>/gallon (5 m<sup>2</sup>/L)

Base coat: 120 ft<sup>2</sup>/batch (3 m<sup>2</sup>/L)

First topcoat:

150 – 375 ft<sup>2</sup>/gallon (3.7 – 9.4 m<sup>2</sup>/L)

Second topcoat:

150 – 375 ft<sup>2</sup>/gallon (3.7 – 9.4 m<sup>2</sup>/L)

All coverage rates are approximate.

Coverage rates will vary with the desired texture and the porosity of the concrete.

## PACKAGING

5 gallon (18.95 L) pails

55 gallon (208 L) drums

Pigment: 1 Pint Can

## COLOR

Clear and 7 standard colors.

Custom colors are available on request.

Custom colors are subject to minimum quantities, increased manufacturing lead-times, and premium pricing. Refer to the Master Builders Solutions Performance Flooring Color Guide for more information.

## SHELF LIFE

MasterTop Epoxy coatings: 2 years when properly stored.

MasterTop TC 493 Polyurethane topcoat: 1 year when properly stored.

MasterTop TC 693 Polyaspartic topcoat: 1 year when properly stored.

## STORAGE

Store and transport in unopened containers in a clean, dry area.

Protect from freezing.

## VOC CONTENT

See MasterTop 1215 AHS LEED Letter

## DESCRIPTION

MasterTop 1215 AHS aircraft hangar floor system is a specially formulated epoxy and polyurethane or polyaspartic coating system. It forms a tough, UV-stable, abrasion-resistant flooring system specifically for use in aircraft hangars.

## PRODUCT HIGHLIGHTS

- Excellent abrasion resistance, ideal for wheeled traffic
- Chemical and stain resistant for easy maintenance
- Glossy, light reflecting finish for increased visibility and a safer work environments

## APPLICATIONS

- Where resistance to aircraft fuels, hydraulic fluids, and rubber tires is required

## TECHNICAL DATA

### COMPOSITION

Specially formulated products consisting of epoxy primer and base coats and polyurethane topcoats.

### TEST DATA

PROPERTY	RESULTS	TEST METHODS
<b>Adhesion</b> , pli	> 30	ASTM D 903
<b>Hardness</b>	H pencil hardness	ASTM D 3363
<b>Salt spray</b> , after 1,000 hours	No effect	ASTM B 117
<b>Accelerated weathering</b> , after 2,000 hours	No effect	ASTM D 822
<b>Moisture vapor</b> , perm inches	0.01	ASTM E 96
<b>Coefficient of friction</b>		ASTM D 2047
Dry	0.74	
Wet	0.73	
<b>Taber abrasion</b> , g loss; 1,000 cycles, CS-17 wheel	0.038	ASTM D 4060

Unless otherwise noted, test samples were cured 7 days at 73° F (23° C). Properties listed represent the complete system. For properties of individual coatings, refer to the appropriate technical data sheet.

### CHEMICAL RESISTANCE

Full chemical resistance is achieved after curing for 7 days. For resistance to a specific chemical compound, consult the MasterTop Chemical Resistance Guide.

## HOW TO APPLY

### SURFACE PREPARATION

- Concrete floors must be structurally sound and fully cured a minimum of 28 days.
- Repair concrete as necessary.
- Use a commercial degreaser to clean floors of oil, grease, and other bond-inhibiting materials.
- Remove curing and parting compounds and other surface hardeners and floor coatings in accordance with the manufacturer's instructions.
- Mechanical surface profiling is the method of surface preparation for both new and existing floors. Mechanically profile the floor to CSP 3 – 4 (approximating medium-grit sandpaper) as described by the International Concrete Repair Institute. Do not use acid etching for surface preparation. Do not use any method that could fracture the concrete.
- Apply a 25 ft<sup>2</sup> (2.35 m<sup>2</sup>) test in an inconspicuous area that meets the owner's expectations for appearance, slip resistance, and performance.

## MIXING

- Mix the components for this product in the following ratios.

### TYPICAL PROPERTIES

APPLICATION COMPONENTS	MIX RATIO BY VOLUME
<b>Primer</b> MasterTop GP 500	2 to 1
<b>Base Coat</b> MasterTop GP 500 Part A / BC 500HT Part B MasterTop PGM 500 pigment pack	2 to 1
<b>Topcoat</b> MasterTop TC 493 Part A / Part B or MasterTop TC 693 Part A / Part B	3 to 1 1 to 1

\*Add 1 pigment pack every 3 mixed gallons\* for the MasterTop 1215 AHS System. Consult the MasterTop Pigment Pack color chart for more information

- Properly mix each component separately before mixing together to ensure uniform consistency.

- Combine Parts A and B in a suitably sized container. Use the proper ratios of A and B; scrape the sides of the containers to ensure a complete reaction.
- Mix properly for 3 minutes with a slow speed drill and Jiffy style mixing paddle at 350 rpms. Keep the paddle below the surface to avoid entrapping air. Do not mix by hand.

### PRIMING

Apply the mixed primer at 200 ft<sup>2</sup>/gallon (5 m<sup>2</sup>/L). Allow to cure.

### APPLICATION

- Add 1/3 gallon (1.26 L) of MasterTop MS 113F silica flour to each 1.5 gallon batch of mixed MasterTop GP 500 (1 1/2 gallon batch (1 gallon PTA to 1/2 gallon PTB) with 1/3 gallon silica flour. Apply at a rate of 120 ft<sup>2</sup> (11.15 m<sup>2</sup>) / batch. Allow to cure.

2. Apply the mixed topcoat at 150 – 375 ft<sup>2</sup>/gallon (25.5 – 34.8 m<sup>2</sup>). Allow to cure.
3. Apply a second topcoat, if required. The floor can be opened to traffic in 24 hours.

#### DRYING TIMES

Primer: 12 – 24 hours

Base coat: 12 – 24 hours

Polyurethane top coat: 18 – 24 hours

Polyaspartic top coat: 4 – 8 hours

Drying times assume 70° F (21° C) and 50% relative humidity.

#### MAINTENANCE

Regular cleaning and maintenance will prolong the life of all polymer flooring systems, enhance their appearance, and reduce any tendency to retain dirt. Refer to the MasterTop cleaning and maintenance guide for more information.

#### BEST PERFORMANCE

- An effective moisture vapor barrier is required for substrates on or below grade; if not present, contact your Master Builders Solutions representative for options.
- MasterTop 1215 AHS should be installed at a substrate temperature from 50 to 85° F (10 to 30° C).
- Do not expose MasterTop 1215 AHS to any chemicals until fully cured (7 days).
- Boxing batches is recommended to ensure color consistency
- The architect and owner should address joint details with the flooring contractor before the job starts.
- Master Builders Solutions representatives and flooring specialists are available to assist you in the selection of the proper flooring system. Call 1-800-243-6739 for in-house and field technical assistance.
- Use pads under vehicle wheels to reduce the possibility of tire-plasticizer migration.
- Precondition this product to 70° F (21° C) for 24 hours before using.
- Do not exceed the recommended recoat window of 24 hours; if in doubt, contact your Master Builders Solutions flooring specialist.
- Make certain the most current versions of product data sheet and SDS are being used; visit [www.master-builders-solutions.com/](http://www.master-builders-solutions.com/)

en-us to verify the most current versions.

- Proper application is the responsibility of the user. Field visits by Master Builders Solutions personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

#### HEALTH, SAFETY AND ENVIRONMENTAL

Health, Safety and Environmental Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.master-builders-solutions.com/en-us](http://www.master-builders-solutions.com/en-us), e-mailing your request to [mbsbscst@mbcc-group.com](mailto:mbsbscst@mbcc-group.com) or calling 1(800)433-9517. Use only as directed.

**IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.**

#### LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC (“Master Builders”) warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are

waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders’ present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

**FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.**