



We create chemistry

9 | 09 67 23
Resinous
Flooring

MasterTop® 1235SL

Self-leveling epoxy flooring system

FORMERLY SELBACLAD™ SL / SLB

YIELD

Primer: 100 – 200 ft²/gallon
(2.5 – 5 m²/L)

Base coat: 60 ft²/batch (5.6 m²/batch)

Top coat: approximately 80 – 125 ft²/
gallon (2 – 3.12 m²/L).

All coverage rates are approximate.

Coverage rates will vary with the desired
texture and the porosity of the concrete.

PACKAGING

5 gallon (18.95 L) pails

55 gallon (208 L) drums

Pigments: 1 Pint (0.5 L) Can

Aggregate: 50 lb (22.5 kg) bags

COLOR

MasterTop 1235 SL is available in 7
standard colors. Custom colors are
subject to minimum quantities and
increased manufacturing lead-times.

See the BASF Performance Flooring Color
Guide for additional information.

SHELF LIFE

MasterTop Epoxy Resins: 2 years when
properly stored.

STORAGE

Store and transport in unopened
containers in a clean, dry area.
Protect from freezing.

VOC CONTENT

See MasterTop 1235SL LEED Letter

DESCRIPTION

MasterTop 1235SL is composed of 100% solids, tinted epoxy resins and specially graded aggregates. It is installed at a thickness from 1/16 – 1/8" (1.5 – 3 mm) or greater. MasterTop 1235SL will handle foot and light wheeled traffic in a variety of industrial and commercial buildings. MasterTop 1235SL can also incorporate a broadcast aggregate for added slip resistance.

PRODUCT HIGHLIGHTS

- Excellent flow and self-leveling properties that are designed for rapid and efficient installation
- Available in smooth and textured finishes that allows slip resistance to be adjusted
- Durable surface coat is easy to clean and maintain
- Epoxy technology provides good chemical resistance
- Wide temperature in-service range makes it ideal for hot or cold environments
- 100% solids epoxy formulation is VOC compliant in all regions and low in odor

APPLICATIONS

- Where abrasion and chemical resistance are required
- Pneumatic pallette-jack areas
- Warehouses
- Food-and-beverage preparation areas
- Clean rooms
- Restrooms
- Locker rooms

LOCATION

- Interior applications

SUBSTRATE

- Over new and existing concrete surfaces or toppings

TECHNICAL DATA

COMPOSITION

MasterTop 1235 SL is composed of 100% solids, tinted epoxy-resin components and specially graded aggregates.

TYPICAL PROPERTIES (CURED)

PROPERTY	VALUE
Weight , lb/ft ² (kg/m ²), at 1/8" (3 mm)	5.86 (28.6)

TEST DATA (CURED)

PROPERTY	RESULTS	TEST METHODS
Compressive strength , psi (MPa)	13,100 (92)	ASTM C 579
Tensile strength , psi (MPa)	9,700 (68)	ASTM D 638
Flexural strength , psi (MPa)	4,990 (34)	ASTM D 790
Surface flammability		ASTM E 162
Flame spread index	9.29	
Smoke deposit, mg/ms	0.1	
NBS Class	1	
Rate of burning	Self-extinguishing	ASTM D 635
Abrasion resistance , CS-17 wheel, 1,000 cycles, 1,000 gram load	0.070 gram loss	ASTM D 4060
Hardness , Shore D	75 – 85	ASTM D 2240
Indentation , inches		MIL-D-3134
Initial	0.007 (0.6%)	
24 hr residual	0.0 (0%)	
Impact resistance	No chipping, cracking or delaminating	MIL-D-3134
Fire resistance	Fire retardant	MIL-D-3134
Adhesive strength , psi (MPa) (100% concrete failure)	350 (2.5)	ASTM D 4541
Slip-resistant properties	Min. 0.8 (exceeds ADA requirements)	MIL-D-3134
Oil absorption	Nil	MIL-D-3134
Water absorption	Nil	MIL-D-3134
Heat resistance	No flow, slip or softening at 158° F (70° C) for 5 hours	MIL-D-3134

Unless otherwise noted, test samples were cured 7 days at 70° F (23° C)

CHEMICAL RESISTANCE

Full chemical resistance is achieved after curing for 7 days. For resistance to specific chemicals, consult the MasterTop Chemical Resistance Guide.

HOW TO APPLY

SURFACE PREPARATION

1. Concrete floors must be structurally sound and fully cured a minimum of 28 days. Test floor for vapor drive in accordance with ASTM D 4263, ASTM F 2170 or ASTM F 2420.
2. Repair concrete as necessary.
3. Use a commercial degreaser to clean floors of oil, grease, and other bond-inhibiting materials.
4. Remove curing and parting compounds and other surface hardeners and floor coatings in accordance with the manufacturer's instructions.
5. Mechanical surface profiling is the recommended method of surface preparation for both new and existing floors. Mechanically profile the floor to CSP 3 – 4 (approximating medium grit sandpaper) as described by the International Concrete Repair Institute. Do not use acid etching for surface preparation. Do not use any method that will fracture the concrete.
6. Apply a 25 ft² (2.35 m²) test in an inconspicuous area that meets the owner's expectations for appearance, slip resistance, and performance.

MIXING

1. Mix the components for this product in the following ratios.

TYPICAL PROPERTIES

APPLICATION COMPONENTS	MIX RATIO BY VOLUME
Primer MasterTop GP 500 Part A / Part B + MasterTop PGM 500 pigment	2 to 1
Base Coat MasterTop GP 500 Part A / Part B + MasterTop PGM 500 pigment + MasterTop SL 500F aggregate	2 to 1
Topcoat MasterTop TC 504 Part A / Part B	2 to 1

*Add 1 pigment pack every 3 mixed gallons (11.35 L) of MasterTop GP 500. (Note: Some colors will require 2 pigment packs for every 3 mixed gallons. Consult the BASF Performance Flooring Color Guide for more information.)

2. Properly mix each component separately before mixing together to ensure uniform consistency.

3. Combine Parts A and B in a suitably sized container. Use the proper ratios of A and B. Scrape the sides of the containers to ensure a complete reaction.
4. Mix properly for 3 minutes with a slow speed drill and Jiffy style mixing paddle at 350 rpms. Keep the paddle below the surface to avoid entrapping air. Do not mix by hand.

APPLICATION

1. Install the appropriate prime coat in a manner suited to the substrate and its profile. Apply at 50 – 200 ft²/gallon (1.25 – 5 m²/L). Allow to cure.
2. Apply the tinted base-coat mixture at a rate of 60 ft²/batch (5.6 m²/batch). Spread with a 1/4" V-notched trowel. Back roll with a loop or spiked roller. Allow the material to self-level and cure.
3. If additional slip resistance is required, broadcast the aggregate into the coating to the point of rejection. Allow to cure, then sweep, stone, and vacuum the excess aggregate. If slip resistant finish is not required, omit this broadcast step.
4. Apply the pigmented finish coat or lock coat. Spread the material by squeegee or trowel and back roll to achieve the desired texture (if used as a topcoat). The total system thickness should be a minimum of 1/16 – 1/8" (1.5 – 3 mm), depending on the specification. Allow to cure.
5. Apply an optional finish coat of pigmented MasterTop TC 493 or MasterTop TC 683, if additional UV or abrasion resistance is required. Note: Various curing agents can be used to achieve desired application properties. Refer to the MasterTop GP 500 product data sheet for more information.

DRYING TIME

Primer: 12 – 24 hours

Base coat: 12 – 24 hours

Topcoat: refer to individual top coat product data guides

Drying times assume 70° F (21° C) and 50% relative humidity.

MAINTENANCE

Regular cleaning and maintenance will prolong the life of all polymer flooring systems, enhance their appearance, and reduce any tendency to retain dirt. Refer to the MasterTop Cleaning and Maintenance Guide for more information.

FOR BEST PERFORMANCE

- Precondition this product to 70° F (21° C) for 24 hours before using.
- Do not exceed the recommended recoat window of 24 hours. If in doubt, contact your BASF flooring specialist.
- Boxing batches is recommended to ensure color consistency.
- For applications over substrates other than concrete, contact BASF Technical Service.
- Do not expose the MasterTop 1235SL flooring systems to any chemicals until fully cured (7 days).
- Use an effective moisture-vapor barrier for substrates on or below grade. If not present, contact your BASF representative for options.
- Do not install over pitched floors.
- MasterTop 1235SL system is not suitable for areas requiring high impact resistance.
- Install these products at a substrate temperature from 50 to 85° F (10 to 30° C).
- Consult the appropriate chemical resistance data for information on resistance to specific chemicals.
- The maximum service temperature is 170° F (76° C).
- Rapid thermal cycling can lead to premature failure of this product.
- BASF representatives and flooring specialists are available to assist you in the selection of the proper flooring system. Call 1-800-243-6739 for in-house and field technical assistance.
- Apply a finish coat of pigmented MasterTop TC 493 or MasterTop TC 683 for increased abrasion resistance, color retention, or stability.
- Make certain the most current versions of product data sheet and SDS are being used; visit www.master-builders-solutions.BASF.us to verify the most current versions.

- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Health, Safety and Environmental Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.basf.us, e-mailing your request to basfbscst@basf.com or calling 1(800)433-9517. Use only as directed. **For medical emergencies only, call ChemTrec 1(800)424-9300.**

LIMITED WARRANTY NOTICE

Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, **BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS**, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all **CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS)**

OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.