

MasterRoc[®] MG 10 NA

High Yield Thixotropic Non-Shrink Grout

Description

MasterRoc MG 10 NA is a thixotropic, high yield, and shrinkage compensated grout used for placement of cable and rock bolts in tunnels and underground mines.

Applications

MasterRoc MG 10 NA grout is suitable for the encapsulation of roof bolts and cable anchors where the “top-down” grouting method is preferred. MasterRoc MG 10 NA grout is specially designed to provide a high yield (volume) of grout mixture without segregation or bleeding that can develop excellent compressive strengths.

Features

- Highly pumpable; yet, exhibits rapid thixotropy
- Can be applied through small-diameter grout tubes
- Excellent strength development
- Extended working time (about 60 minutes at 68 °F [20 °C])
- Excellent bond to steel and surrounding strata

Benefits

- Restricted flow into surrounding strata
- Enables the use of smaller drill holes
- Eliminates the requirement for sealing of the collar and plate with cotton waste etc.
- Economical to use
- Enhances the safety of critical bolt and anchor installations

Performance Characteristics

Technical data

Compressive strength (Typical)*:

Age	Compressive Strength**
1 day	> 5,000 psi (35 MPa)
7-day	> 8,500 psi (60 MPa)
28-day	>11,500 psi (80 MPa)

* Strength development of grout is dependent on the amount of mixing water, ambient temperature, age and curing of the grout mixture. Actual results may vary.

** ASTM C109/C109M Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (using 2 in. [50 mm] Cube Specimens). Samples made with 44 lb (20 kg) of MasterRoc MG 10 NA grout and 1.7 gal (6.5 L) of water, at 73 °F (23 °C)

Guidelines for Use

Application Procedure: MasterRoc MG 10 NA grout is supplied ready to use; requiring only the addition of potable water.

Mixing 44 lb (20 kg) of MasterRoc MG 10 NA grout with 1.7 gal (6.5L) of water will yield approximately 3.6 gal (13.5 L) or 0.5 ft³ (0.0135 m³) of grout mixture.

Mixing Equipment: For best results, a high mechanical shear mixer or a paddle mixer should be used to mix MasterRoc MG 10 grout. The grout pump used must have accurate water dosing capabilities.

Mixing Procedure: Fill the mixer with the correct amount of water that matches the number of bags of MasterRoc MG 10 NA grout. As a guide, use 1.7 - 2.0 gal (6.5 - 7.5L) of water per 44 lb (20 kg) bag of MasterRoc MG 10 NA grout for a thixotropic mixture. The actual amount of water required will depend on the desired consistency of the grout mixture and the grout pump available. Do not exceed the amount of water recommended for obtaining thixotropic mixtures.

Start the mixer after adding the required amount of water. Slowly add MasterRoc MG 10 grout powder. Continue mixing until a thick, creamy, no-lump consistency is obtained.

Discard any grout mixture that has been left unattended for more than 60 minutes. Do not retemper.

Cleaning: As with all grouting operations, it is essential to systematically clean the pump and grout lines with clean water. This should be done immediately after completion of grouting operations. If the grouting operations delay for more than an hour, the batched grout mixture should be discarded, and the pump and grout lines cleaned.

Storage and Handling

Shelf Life: MasterRoc MG 10 NA grout needs to be stored in a dry place. When properly stored, MasterRoc MG 10 NA grout has a minimum shelf life of 12 months.

Safety: Standard precautions for handling chemical products should be observed. Avoid eye and skin contact and wear hand gloves and safety goggles. If contact occurs, rinse with plenty of water. In case of eye contact, seek medical advice. For further information, refer to the Safety Data Sheet.

Packaging

MasterRoc MG 10 NA grout is supplied in 44 lb (20 kg) moisture resistant bags.

Related Documents

Safety Data Sheets: MasterRoc MG 10 NA grout

Additional Information

For additional information on the MasterRoc MG 10 NA grout, contact your local sales representative.

Master Builders Solutions, a brand of MBCC Group, is a global leader of innovative chemistry systems and formulations for construction, maintenance, repair and restoration of structures. The Admixture Systems business provides advanced products, solutions and expertise that improve durability, water resistance, energy efficiency, safety, sustainability and aesthetics of concrete structures, above and below ground, helping customers to achieve reduced operating costs, improved efficiency and enhanced finished products.

Utilizing worldwide resources, the Master Builders Solutions community of experts are passionate about providing solutions to challenges within all stages of construction, as well as the life cycle of a structure. At Master Builders Solutions we create sustainable solutions for construction around the globe.

Limited Warranty Notice

Master Builders Solutions Admixtures US, LLC ("Master Builders Solutions") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.