

MasterRoc[®] MP 300

Low viscosity, flexible acrylic resin with adjustable set times and adjustable water to resin levels specially formulated for repairs of dams, sewer and storm pipe systems, and for pre-excavation grouting, strata control and soil permeation grouting.

Description

MasterRoc MP 300 product is a versatile, low viscosity resin that facilitates adjustable set times with adjustable water to resin contents. MasterRoc MP 300 product forms a flexible crosslinked gel with excellent adhesive properties. MasterRoc MP 300 product retains its excellent swelling property in the presence of water, even after dry periods.

Applications

Recommended for use in:

- Sealing and consolidation in damp or wet areas
- Concrete repair
- Box culvert joint repair
- Storm and sewer pipe sealing
- Permanent water sealing of tunnels, shafts, concrete linings and masonry
- Pre-excavation injection

Features

- Acrylamide-free
- Re-swells upon exposure to moisture after dry periods
- Cured material is a highly flexible gel
- Excellent adhesive properties, even on damp or wet surfaces
- Resistant to acidic and alkaline solutions, as well as many other solvents
- Very low viscosity (close to that of water)
- Controllable gel time (between 10 seconds and 30 minutes at 68 °F (20 °C))
- Can be used with colored dye for better detection
- Environmentally preferable

Benefits

- Swelling-fitted filling of cracks and fissures
- Can accommodate structural and ground movements
- Self-heals even after dry periods
- Very low viscosity helps in deep penetration of the product into very fine cracks or fissures and long flow paths, even at low pressure
- Harmless when in contact with groundwater, with no emission of dangerous substances

Performance Characteristics

Technical Data

MasterRoc MP 300 Resin

Appearance:	Light brown liquid
Density*:	10.0 lb/gal (1.2 kg/L)

MasterRoc MP 300 Accelerator

Appearance:	Clear liquid
Density*:	9.0 lb/gal (1.075 kg/L)

MasterRoc MP 300 Hardener

Appearance:	White powder
-------------	--------------

Mixed material (Part A and Part B)

Appearance:	Light brown liquid
Viscosity*:	2 - 5 mPa·s (cP), depending on mixing ratio
Density*:	8.3 lb/gal (1.0 kg/L)

*@ 68°F (20°C)

Guidelines for Use

Dosage and Application Procedure: Part A (activated resin) and Part B (activated hardener) have to be prepared prior to injection, based on the desired gel time. To prepare Part A, mix MasterRoc MP 300 Resin with MasterRoc MP 300 Accelerator. Part A can also be prepared with a 1:1 mixture of MasterRoc MP 300 Resin and water, and MasterRoc MP 300 Accelerator. To prepare Part B, dissolve MasterRoc MP 300 Hardener powder in water. Part of the water in Part B can be replaced with MasterRoc Part B Latex if increased density of the cured gel is required. Please contact your local Master Builders Solutions Sales Representative for additional information or guidance.

Table 1 below shows the dosage of accelerator in relation to the gel time at different temperatures (Using a 4% hardener solution as Part B).

Table 1: MasterRoc MP 300 Accelerator dosages vs Gel times

Accelerator Dosage		Gel Time, min:s	
Percent by Mass of Resin	fl oz/gal (mL/L) of Resin	50 °F (10 °C)	70 °F (21 °C)
3.0	4.3 (33.5)	1:45	1:30
4.0	5.7 (44.7)	1:05	0:55
5.0	7.1 (55.8)	0:55	0:40
6.0	8.6 (67.0)	0:45	0:35
7.0	10.0 (78.1)	0:35	0:30
8.0	11.4 (89.3)	0:30	0:25
10.0	14.3 (111.6)	0:25	0:20
12.0	17.1 (134.0)	0:20	0:18
15.0	21.4 (167.4)	0:17	0:15

Note: Gel time is dependent on the solid content of the hardener solution, amount of accelerator added, temperature of the activated components, and the temperature of the ground or structure. For information on getting gel times outside of the range shown in Table 1, please contact your local Master Builders Solutions Sales Representative.

The following example illustrates how to prepare Part A and Part B to get a gel time of 30 seconds at a temperature of 70 °F (21 °C), with 44 lb (20 kg) pail of MasterRoc MP 300 Resin.

To prepare Part A, mix one pail (44 lb (20 kg)) of MasterRoc MP 300 Resin with 52 fl oz (1.3 L) of MasterRoc MP 300 Accelerator (which is around 7% of the resin by mass).

To prepare Part B, dissolve 27 fl oz (1.7 lb or 0.8 kg) of MasterRoc MP 300 Hardener in 4.9 gal (18.3 L) of water.

The activated components are injected in the ratio of 1:1 by volume, using a two-component injection pump, equipped with a static in-line mixer.

The activated resin (Part A) and the activated hardener (Part B) have a pot life of approximately 8 hours at 68 °F (20 °C).

Cleaning: Injection equipment and hoses can be cleaned of uncured material using water (if possible, with a detergent).

Storage and Handling

Storage Temperature: MasterRoc MP 300 product components should be kept in a dry place within a temperature range of 40 °F to 85 °F (5 °C to 30 °C) and be protected from direct sunlight. In unopened, tightly closed containers, the components of MasterRoc MP 300 product can be stored for up to 12 months.

Prolonged exposure to sunlight and high temperatures (above 85 °F (30 °C) may cause the MasterRoc MP 300 product components to solidify.

Caution: Do not let MasterRoc MP 300 Accelerator and MasterRoc MP 300 Hardener to come in contact with each other directly prior to field mixing, as the exothermic reaction between the two can result in fire.

MasterRoc MP 300 Accelerator and MasterRoc MP 300 Hardener are not compatible with aluminum and hence, aluminum equipment or tools should not be used to handle them.

Safety: Avoid contact with skin and eyes by using the required personal protective equipment, such as waterproof boots, overalls, gloves and safety glasses.

If contact with skin occurs, wash thoroughly using soap and water. If contact with eyes occurs, rinse thoroughly with water and seek medical advice. The cured MasterRoc MP 300 product is harmless.

Uncured products should be prevented from entering local drainage systems and water courses. Spillage must be collected using absorbent materials such as sawdust and sand and, disposed of in accordance with local regulations.

Refer to the Safety Data Sheet for further safety measures

Packaging

MasterRoc MP 300 Resin: 44 lb (20 kg) (4.4-gal (16.7L)) pail

MasterRoc MP 300 Accelerator: 6.6 lb (3 kg) bottle

MasterRoc MP 300 Hardener: 2.2 lb (1.0 kg) bottle

Related Documents

Safety Data Sheets: MasterRoc MP 300 (Resin, Accelerator and Hardener)

Additional Information

For additional information on MasterRoc MP 300 product, contact your local sales representative.

Master Builders Solutions, a brand of MBCC Group, is a global leader of innovative chemistry systems and formulations for construction, maintenance, repair and restoration of structures. The Admixture Systems business provides advanced products, solutions and expertise that improve durability, water resistance, energy efficiency, safety, sustainability and aesthetics of concrete structures, above and below ground, helping customers to achieve reduced operating costs, improved efficiency and enhanced finished products.

Utilizing worldwide resources, the Master Builders Solutions community of experts are passionate about providing solutions to challenges within all stages of construction, as well as the life cycle of a structure. At Master Builders Solutions we create sustainable solutions for construction around the globe.

Limited Warranty Notice

Master Builders Solutions warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.