

03 30 00	Cast-in-Place Concrete
03 37 13	Shotcrete
03 37 16	Pumped Concrete

MasterRoc® MS 675

Lubricating Aid, Viscosity Modifier and Strength Enhancer for Shotcrete and Concrete

Description

MasterRoc MS 675 is a liquid dispersion of nanometric colloidal silica, designed to improve the properties of shotcrete and concrete in both the plastic and hardened states. MasterRoc MS 675 product meets ASTM C 494/C 494M requirements for Type S, Specific Performance, admixtures.

Applications

MasterRoc MS 675 product is used for improving the physical and mechanical performance of pumped concrete, shotcrete and conventionally placed concrete.

Features

- Very low viscosity
- Normal setting characteristics
- Reduced bleed characteristics
- Reduced segregation, particularly in lean mixtures and high slump concrete mixtures

Benefits

- Enhanced workability and stability
- Improved pumpability, especially over long distances
- Improved sprayability of shotcrete, including a reduction of rebound
- Improved strength and durability of concrete mixtures
- Reduction in shrinkage of hardened concrete

Performance Characteristics

Technical Data

Typical values

Color	Clear
Viscosity*	7 cP (mPa.s)
Density*	75.0 lb/ft ³ (1.2 kg/L)
pH*	10.5
SiO ₂ concentration	30 ± 1 %

*@ 68 °F (20 °C)

Applications

Viscosity Modifier

Due to its ultrafine particle size, MasterRoc MS 675 product “completes” the grading curve within flowing concrete, self-consolidating concrete and shotcrete mixtures. This greatly improves the cohesiveness within the high flow mixtures and prevents segregation and bleeding. The inclusion of MasterRoc MS 675 product also improves the surface finish.



Strength Enhancer

Both the compressive and flexural strengths can be improved by optimizing the mixture and incorporating MasterRoc MS 675 product along with a polycarboxylate-based water-reducing admixture. Normally, a typical concrete mixture achieves a flexural strength that is about one-tenth of its compressive strength, while the optimized mixture can achieve an improved ratio.

Lubricating Aid

The inclusion of MasterRoc MS 675 product in pumped concrete and shotcrete offers improved pumpability and reduced pumping pressures, especially in mixtures with low cement content, lack of fines and poorly-graded aggregates.

Guidelines for Use

Dosage: The recommended dosage range of MasterRoc MS 675 product is 4 to 12 fl oz/cwt (260 to 780 mL/100 kg).

The dosage of MasterRoc MS 675 product will vary according to the quantity of fines within a mixture and the resultant rheology required for the application. Preliminary tests are recommended to determine the optimum dosage.

Please consult your local Master Builders Solutions technical representative for guidance, if dosages outside those recommended are required.

Dispensing and Mixing: MasterRoc MS 675 product should be incorporated in the mixing water. MasterRoc MS 675 product should not be added to the dry materials.

Product Notes

Compatibility: MasterRoc MS 675 product can be used with other Master Builders Solutions admixtures to achieve cost-effective customized performance. However, all admixtures should be dispensed separately to ensure complete distribution throughout the mixture. MasterRoc MS 675 product should not be used in conjunction with other admixtures unless specific test information is available.

Storage and Handling

Storage Temperature: MasterRoc MS 675 product should be stored within a temperature range of 40 °F and 95 °F (5 °C and 35 °C). Do not allow the product to freeze. Consult your local Master Builders Solutions technical representative before using any product that has frozen. Store under cover, out of direct sunlight and protect from extremes of temperature.

Safety: MasterRoc MS 675 product contains no hazardous materials requiring labeling. However, colloidal silica will irritate the eyes and the skin. Hence, standard precautions for handling chemical products should be observed: Avoid eye and skin contact and wear gloves and safety goggles. If contact occurs, rinse with plenty of water. In case of eye contact, seek medical advice.

Packaging

MasterRoc MS 675 product is available in bulk and packaged quantities. Because bulk shipping and packaging sizes vary by region, please contact your local Master Builders Solutions sales representative for more information.

Related Documents

Safety Data Sheets: MasterRoc MS 675 product.

Additional Information

For additional information on MasterRoc MS 675 product, contact your local sales representative.

Master Builders Solutions creates technologies for the construction industry inspiring people to build better. We are active in ~40 countries and operate 35 production sites with over 1,600 employees. We develop, produce, and market high-quality chemical admixtures, as well as adjacent core technologies, to master the challenges of today and support a decarbonized future. Our people are pivotal and pair leading technologies and a strong brand heritage to surpass our customers' expectations and drive continuous value creation.

Limited Warranty Notice

Master Builders Solutions Admixtures US, LLC ("Master Builders Solutions") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. **MASTER BUILDERS SOLUTIONS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS.** The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders Solutions. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. **MASTER BUILDERS SOLUTIONS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.**

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders Solutions' present knowledge and experience. However, Master Builders Solutions assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders Solutions reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.