

A/BC Base Coat

100% acrylic adhesive and base coat

PACKAGING

27.2 kg per 19-liter pail
(60 lbs per 5-gallon pail)

COVERAGE

Approximate coverage rates are as follows:

1. Adhere EPS insulation board to substrate: 14.8 m² (160 ft²) per pail via notched trowel method, 16.7 m² (180 ft²) per pail via ribbon & dab method
2. Embed Finestone Standard Reinforcing Mesh: 26 m² (280 ft²) per pail, Embed Intermediate 12: 18.5 m² (200 ft²) per pail, Embed Hi-Impact 20 & Finestone Standard Reinforcing Mesh 14.8 m² (160 ft²) per pail
3. Adhere EPS insulation board to substrate and embed Finestone Standard Reinforcing Mesh 11.1 m² (120 ft²) per pail

DESCRIPTION

100% acrylic adhesive and base coat that is field-mixed with Type I or Type II Portland cement. Very creamy texture that spreads easily.

USES

1. For use with the Pebbletex Wall System to adhere expanded polystyrene insulation board to the following acceptable substrates: Finestop RA, Finestop RS, Finestop VB, PermaBase[®] Cement Board and other cement boards conforming with ASTM C1325 (Type A - exterior); poured concrete/unit masonry; ASTM C1177 type sheathings, including Weather Defense[™] Platinum sheathing, GreenGlass[®] sheathing, eXP[™] sheathing, GlasRoc[®] sheathing, Securock[™] glass-mat sheathing, and DensGlass[®] exterior sheathing; gypsum sheathing (ASTM C79/C1396); Exposure I or exterior plywood (Grade C/D or better); or Exposure I OSB.
2. To adhere expanded polystyrene insulation board to expanded polystyrene insulation board.
3. For use with Pebbletex, Pebbletex D, D7 and D10, Finestone Finescreen System and all Finestone Surfacing Systems to embed Corner Mesh and Finestone Reinforcing Mesh.

MIXING

1. Prepare in a container which is clean and free of foreign substances. Do not use a container which has contained or been cleaned with a petroleum-based product.
2. Mix the contents of the A/BC Base Coat pail with a low speed drill and paddle mixer until thoroughly blended. Mix one part (by weight) Portland cement with one part A/BC Base Coat. Add Portland cement in small increments, thoroughly mixing to a homogeneous consistency after each additional increment.
3. Clean, potable water may be added to adjust workability.
4. Let stand for 5 to 10 minutes, then remix and retemper before use.
5. Additives are not permitted.
6. Close container when not in use.
7. Clean tools with soap and water immediately after use.

FEATURES

Smooth, creamy consistency

Familiar 1:1 mixing ratio

100% Acrylic

Water based

BENEFITS

Trowels on easily, speeds mesh embedment, reduces applicator arm fatigue, increases job-site productivity

Easy to mix—less chance of error

Provides long-term durability

Safe, non-toxic, clean up easily with soap & water

APPLICATION

TO ADHERE EPS TO ACCEPTABLE SUBSTRATES OR TO OTHER EPS:

Notched trowel method—Apply mixed A/BC Base Coat to entire surface of insulation board using a stainless steel trowel with 13 mm x 13 mm (1/2" x 1/2") notches spaced 13 mm (1/2") apart, or 10 mm x 10 mm (3/8" x 3/8") notches spaced 10 mm (3/8") apart.

-OR-

Ribbon & dab method—Apply a ribbon of mixed A/BC Base Coat approximately 50 mm (2") wide by 10 mm (3/8") thick to entire perimeter of each board with a trowel. Apply dabs or ribbons of 10 mm (3/8") thickness by 100 mm (4") in diameter, approximately 200 mm (8") o.c. over entire surface of board to ensure uniform contact and high initial grab.

Note: Ribbon & dab method is not recommended on gypsum sheathing substrates or DensGlass Gold®. Allow application of insulation board to dry (normally 8 to 10 hours) prior to application of A/BC Base Coat/Reinforcing Mesh.

TO ADHERE EPS TO APPROVED SUBSTRATES ON SENERFLEX PEBBLETEX CI-DCA OPTION ONLY:

Apply to solid surface of insulation board using a stainless steel trowel with 13 mm x 13 mm (1/2" x 1/2") notches spaced 50.8 mm (2") apart, with the notches installed vertically [parallel to the 50.8 mm (2") dimension]. Allow application of EPS insulation board to dry (normally 8 to 10 hours) prior to application of A/BC Base Coat/Reinforcing Mesh.

AS A BASE COAT FOR EMBEDDING

REINFORCING MESH:

A/BC Base Coat shall be applied so as to achieve Reinforcing Mesh embedment with no reinforcing Mesh color visible. Ensure Reinforcing Mesh is free of wrinkles. Allow A/BC Base Coat with embedded Reinforcing Mesh to dry hard (normally 8 to 10 hours) prior to application of Finestone Primer or Finish.

LIMITATIONS

1. Requires job-site mixing. Must be used after mixing.
2. Protect Finestone materials during transportation and storage to avoid physical damage.
3. Store Finestone materials in a cool, dry place protected from freezing. Store at no less than 4 °C (40 °F). Protect from extreme heat and direct sunlight. Shelf life is two years when unopened and stored as directed.
4. Do not apply Finestone materials in ambient temperatures below 4 °C (40 °F). Provide supplemental heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 4 °C (40 °F) prevail.
5. Do not apply Finestone materials to frozen surfaces.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting finestone.master-builders-solutions.com/en, e-mailing your request to mbsbscst@mbcc-group.com or calling +1 (800) 433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

VOC CONTENT

0 g/l, or 0 lbs/gal less water and exempt solvents.

TECHNICAL SUPPORT

Consult Master Builders Solutions Technical Services Department at +1 (800) 589-1336 for specific recommendations concerning all other applications. Consult the Wall Systems website at finestone.master-builders-solutions.com/en, for additional information about products and systems and for updated literature.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but

also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

For the most current version of this literature, please visit our website at finestone.master-builders-solutions.com/en.