



We create chemistry

# Color Coat

100% acrylic-based coating

## Product Bulletin

### DESCRIPTION

100% acrylic-based coating. Designed for spray-, roller- or brush-application over any BASF Wall Systems with minimum change in finish texture or sheen.

### COLORS

Available in standard and custom colors

### PACKAGING

24.9 kg per 19-liter pail  
(55 lbs per 5-gallon pail)

### COVERAGE

Approximate coverage rate:  
69.6–116.1 m<sup>2</sup> (750–1,250 ft<sup>2</sup>)  
per pail (one-coat application)  
may vary. Applications over  
concrete and masonry require  
two coats.

### USES

Color Coat is intended for use as a coating for exterior wall surfaces such as concrete, stucco, unit masonry, acrylic base coat in sealant joints and to change the color of compatible textured finish.

**Note: Color Coat is not intended for use as a finish directly over a BASF Wall Systems' EIFS Base Coat and is not recommended for touch-up.**

### SURFACE PREPARATION

Substrates must be clean, dry, sound and free of loose material, releasing agents, paint, efflorescence, contaminants and other coatings. Cracks or voids must be filled with MasterProtect® FL 746/ FL 748 or appropriate, compatible material to provide a solid substrate prior to application of COLOR COAT. Ensure patching material is dry prior to application of COLOR COAT.

#### Concrete:

1. Allow concrete to cure a minimum of 28 days prior to application of COLOR COAT.
2. Remove all projections and form lines.
3. When needed, apply BASF TINTED PRIMER to cured concrete with a sprayer, 3/8" (10mm) nap roller or good-quality latex paint brush at a rate of approximately 150–250 ft<sup>2</sup> per gallon (3.6–6.1 m<sup>2</sup> per 3.8 liter). BASF TINTED PRIMER shall be dry to the touch before proceeding to the COLOR COAT application.

#### Unit masonry:

1. Allow unit masonry to cure prior to application of COLOR COAT
2. Remove all loose mortar and projections.
3. When needed, apply a leveling coat of BASF Base Coat to provide a smooth surface prior to application of COLOR COAT.

### MIXING

1. Mix the contents of the COLOR COAT pail with a low speed drill and paddle mixer until thoroughly blended.
2. A small amount of clean, potable water may be added to adjust workability, but is generally unnecessary since a thick consistency is desired.
3. Additives are not permitted.
4. Close container when not in use.
5. Clean tools with soap and water immediately after use.

### APPLICATION

#### Graphics/color change:

1. Apply COLOR COAT with a 10 mm (3/8") nap roller or airless spray equipment. If necessary, cut in the edges with a high-quality, latex-type paint brush.
2. Brush or roll out in all directions, maintaining a wet edge at all times.
3. COLOR COAT must be worked continuously until a uniform appearance is obtained over the entire wall surface.
4. For two-coat applications: Allow the first coat to dry prior to application of the second coat.  
-OR-  
Apply the first coat as a tack coat; while maintaining a wet edge, double-back with the second coat.

### Advantages

100% Acrylic chemistry provides optimal performance against elements

Formulated to match the sheen of BASF Wall Systems' finishes, minimizes changes in the aesthetics of the building

Smooth coating that makes minimal change to the texture of the wall

## Color Coat

### To prepare a sealant joint for sealant application:

1. Apply COLOR COAT to the Base Coat in the joint with a high-quality, latex-type paint brush.
2. COLOR COAT must be worked continuously until a uniform appearance is obtained.
3. Allow COLOR COAT to dry thoroughly (approximately 24 hours) prior to application of sealant primer and sealant.

### LIMITATIONS

1. Protect BASF Wall Systems' materials during transportation and installation to avoid physical damage.
2. Store BASF Wall Systems' materials in a cool, dry place protected from freezing. Store at no less than 40 °F (4 °C). Protect from extreme heat and direct sunlight. Shelf life is two years when unopened and stored as directed.
3. Do not apply BASF Wall Systems' materials in ambient temperatures below 40 °F (4 °C). Provide supplementary heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 40 °F (4 °C) prevail.
4. Protect work from precipitation until dry.
5. Do not apply BASF Wall Systems' materials to frozen surfaces.

### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.senergy.basf.com](http://www.senergy.basf.com). Use only as directed.

### VOC Content

<50 g/l less water and exempt solvents.

**For medical emergencies only call chemtrec at (800) 424-9300**

### TECHNICAL INFORMATION

Consult our Technical Services Department for specific recommendations concerning all other applications. Consult the Senergy website, [www.senergy.basf.com](http://www.senergy.basf.com), for additional information about products and systems and for updated literature.

### WARRANTY

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Product Bulletin, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. In the absence of an extended warranty issued by BASF, any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.