



We create chemistry

Leveling Skimcoat

Sandable skim coat for use with BASF Metallic Top Coat

Product Bulletin

PACKAGING

70-lbs per 5-gallon pail
(32-kg per 19-liter pail)

COVERAGE

280 ft² (26 m²) per pail, applied
in two coats

200 ft² (19 m²) per pail, applied
in three coats

COLOR

Light gray

SHELF LIFE

2 years when stored in the
original, unopened conditions
in a cool, dry place away from
direct sunlight. Store at minimum
40°F (4°C). Do not allow
temperature to exceed 120°F
(49°C).

FOR PROFESSIONAL USE ONLY

A preconstruction meeting is
recommended to ensure that
expectations of all parties are
aligned prior to commencing
application. A jobsite mock-up
is also recommended to qualify
workmanship.

DESCRIPTION

BASF LEVELING SKIMCOAT is a sandable skim
coat that is specifically formulated for use with
BASF METALLIC TOP COAT.

USES

BASF LEVELING SKIMCOAT is intended for use
in exterior and interior applications. In exterior
applications, it can be used with BASF Continuous
Insulation, EIFS and stucco wall systems. BASF
LEVELING SKIMCOAT can be sanded to create
a uniform substrate for application of BASF
METALLIC TOP COAT.

EQUIPMENT

- Spiral or Jiffler type mixer paddle
(dedicated/clean)
- Heavy duty 1/2 inch variable speed drill
- Stainless steel tapered Venetian trowel
- Ancora .817/RS-1 tapered soft plastic trowel
(www.wind-lock.com) or equal
- Hand-held misting sprayer
- Drywall hand sander
- 100 and 150 grit drywall sandpaper
- Foam block sanders
- Orbital oscillating hand sander (optional)
- 3M Tack Cloth, Norton Abrasives microfiber
tack cloth or equal

Recommended trowels

First coat: Stainless steel tapered 12x4
Venetian trowel

Second coat: Stainless steel tapered 12x4
Venetian trowel for initial application. Flexible
plastic Venetian trowel to create the final smooth
appearance. Ancora makes a plastic trowel (article
number .817/RS-1, available from Wind-Lock)
that has been found to work well. **NOTE: Use of
standard EIFS/stucco trowels (either new
or broken-in) may result in uneven finish
application.**

MIXING

Mix by using a clean spiral or Jiffler style mixer
with a low speed drill. **NOTE: Do not use drywall
mixing paddles.** Wipe sides of pail down with a
water soaked rag to help eliminate dried particles
from falling into the product. Mist a small amount
of water over unused material before replacing the
lid. Replace lid when not being used.

SUBSTRATE PROTECTION

Ensure that flashing, parapet caps and other
means of protection are installed prior to
application of BASF LEVELING SKIMCOAT, so
that moisture does not accumulate behind BASF
LEVELING SKIMCOAT during construction.

SURFACE PREPARATION

The surface should not contain irregularities. All
divots, pits, mesh overlaps, and mesh patterns
must be leveled and skimmed with a BASF Base
Coat to correct any imperfections.

**NOTE: To ensure a smooth surface, an
additional layer of base coat is required
prior to application of BASF LEVELING
SKIM COAT. All leveling corrections must
be made using base coat. Do not rely on
LEVELING SKIMCOAT to correct base coat
imperfections.**

APPLICATION CONDITIONS

**NOTE: Provide full tenting to protect from
wind and sun.**

APPLICATION

Two coats of LEVELING SKIMCOAT are required.
Three or more coats may be needed to attain the
desired level of surface smoothness.

1. Sand or stone existing surfaces to remove
imperfections and trowel marks. Remove dust
and debris.

Leveling Skimcoat

2. Apply BASF TINTED PRIMER at a rate of 150-250 ft²/gal (14-23 m²/l). The color of BASF TINTED PRIMER is not important. Use of unpigmented BASF TINTED PRIMER tint base is acceptable. Allow primer to dry.
3. Apply the first coat of BASF LEVELING SKIMCOAT using a 12x4 inch Venetian trowel at a uniform thickness of 10-15 mils. Maintain a wet edge at all times during application. Application thickness is critical. Where insufficient thicknesses are applied, rapid drying may result. Excessive thickness may cause check cracking.
4. Allow the first coat of BASF LEVELING SKIMCOAT to partially cure, then sand the skim coat with 100-150 grit sandpaper to remove trowel marks and create a smooth surface. Change sandpaper frequently. For best results, sand BASF LEVELING SKIMCOAT using a sanding block on the same day that it is applied, before it is fully cured.
5. Use a soft brush to remove dust, then wipe the sanded surface with a clean tack cloth to remove dust.
6. Extra care is needed with power sanders. If they are used, rotate sander in a figure-8 pattern to avoid creating a sanding pattern. Avoid sanding deep holes into the BASF LEVELING SKIMCOAT surface.
7. **Insufficient BASF LEVELING SKIMCOAT thickness can result in blister formation in subsequently applied BASF METALLIC TOP COAT.** If heavy sanding is needed to attain a smooth surface, reskim the entire panel with BASF LEVELING SKIMCOAT as outlined in Steps 3 to 5 above.
8. Use a soft brush to remove dust, then wipe the sanded surface with a clean tack cloth to remove dust.
9. For the second and subsequent coats, a small amount of cool, clean, potable water may be used to adjust workability. **Do not add more than 10 oz of water per full pail of BASF LEVELING SKIMCOAT.**
10. Apply the second and subsequent coats in thin (8-12 mil) applications, using the stainless steel trowel. Additional trowel pressure will be needed to ensure adhesion of the second and subsequent coats. Freestyle leveling is not recommended, since it can result in wavy surfaces that become evident in critical light.
11. Manipulate the second and subsequent skim coat applications using the flexible, plastic trowel to obtain a smooth, trowel-line free application. While manipulating the thin second and subsequent coats, be prepared to mist the surface of BASF LEVELING SKIMCOAT and the face of the trowel with clean potable water, using a hand-held spray bottle. This will help maintain a wet edge if the skim coat begins to set before application is complete. Manipulate the surface until it is smooth, achieving a trowel line free application.
12. Allow the second and subsequent coats of BASF LEVELING SKIMCOAT to partially cure, then sand the skim coat with 100-150 grit sandpaper to remove trowel marks and create a smooth surface. Change sandpaper frequently. For best results, sand BASF LEVELING SKIMCOAT using a sanding block on the same day that it is applied, before it is fully cured.
13. Wipe the sanded surface with a clean tack cloth or slightly dampened microfiber cloth to remove dust.
14. Allow the final coat to cure for minimum 8-hours at ambient temperature greater than 50°F (10°C) and relative humidity less than 70%. If ambient temperature is less than 50°F (10°C) or humidity is greater than 70%, allow 24-hour dry time at minimum 40°F (4°C). Protect from rain and other moisture sources while curing.
15. **Insufficient BASF LEVELING SKIMCOAT thickness can result in blister formation in subsequently applied BASF METALLIC TOP COAT.** If heavy sanding is needed to attain a smooth surface, reskim the entire panel with BASF LEVELING SKIMCOAT as outlined in Steps 3 to 9 (two applications) above.
16. Wipe the sanded surface with a clean, clean tack cloth or slightly dampened microfiber cloth to remove dust.
17. After applying the final coat, use 100-150 grit sandpaper to create an ultra smooth surface.
18. Allow BASF LEVELING SKIMCOAT to cure as described in Step 10. Wipe the sanded surface with a clean tack cloth or slightly dampened microfiber cloth to remove dust in preparation for application of BASF METALLIC TOP COAT.

LIMITATIONS

1. Limit the size of each panel to 24 ft² (2.2 m²), with no more than an 8 ft (2.4 m) panel length.
2. Attempting to create a smooth surface on large panels using a scissors or boom lift is not recommended. Large projects that employ BASF LEVELING SKIMCOAT must be scaffolded. In addition to facilitating a more controlled application of BASF LEVELING SKIMCOAT, protection from wind and intense sunlight will be needed for subsequent application of BASF METALLIC TOP COAT.
3. Protect BASF materials during transportation, storage and installation to avoid physical damage.
4. Air and substrate temperatures must be greater than 40°F (4°C) and less than 100°F (38°C) during application, and must be greater than 40°F (4°C) for the following 24 hours.
5. Do not apply BASF LEVELING SKIMCOAT to hot surfaces or in direct, intense sunlight.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting the Wall Systems website at www.wallsystems.basf.com. Use only as directed.

VOC Content

<50 g/L less water and exempt solvents.

For medical emergencies only call chemtrec at (800) 424-9300

WARRANTY

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Product Bulletin, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. In the absence of an extended warranty issued by BASF, any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

Product Bulletin

Leveling Skimcoat

For the most current version of this literature, please visit our website at www.wallsystems.basf.com.