

MaxGrip Veneer Mortar

High-strength specially formulated setting bed mortar used to adhere natural and manufactured stone, tile, and thin brick veneer

PACKAGING

50 lbs per bag (22.6 kg per bag)

YIELD

SOLID LAYER APPLICATION

for stone and thin brick veneers

3/16" thickness:

20–23ft² (1.9–2.1m²)

1/4" thickness:

16–18ft² (1.5–1.7m²)

3/8" thickness (Stone):

10–12ft² (0.9–1.1 m²)

NOTCHED APPLICATION

for tile

1/4" x 3/8" Notched Trowel

55–65 ft² (5.1–6.0 m²)

1/2" x 1/2" Notched Trowel

35–45 ft² (3.2–4.2m²)

SKIMCOAT

1/16" thickness:

60–70 ft² (5.6–6.6 m²)

Note: When estimating material requirements, consider both material required for skim coat plus the material applied to the veneer.

Shelf life is one year when unopened and stored as directed.

DESCRIPTION

Dry-mix polymer-modified setting bed mortar that contains Portland cement.

USES

For use to adhere thin brick veneer, natural and manufactured stone, and tile with Master Builders Solutions Adhered Drainage CI, Non Insulated Stucco and Cement Board Systems. Additional acceptable substrates: Portland Cement Plaster (Stucco) scratch or brown coat complying with ASTM C 926, PermaBase® Cement Board and other cement boards conforming with ASTM C1325 (Type A - exterior), poured and precast concrete/unit masonry.

Note: Approved over Master Builders Solutions - Wall Systems air/water-resistive barriers on masonry units and concrete

MIXING

1. Prepare to mix one bag in a 5-gallon (19-liter) pail that is clean and free of foreign substances. Do not use pails that have contained or been cleaned with a petroleum-based product.
2. Add the following amount of clean, potable water to a pail:
For skim coat or thin brick veneer:
1.0–1.5 gallons (3.8–4.7 liters).
Stone and tile: 0.75–1.25 gallons (2.8–3.8 liters).
3. Add a full bag of MaxGrip Veneer Mortar to the pail in small increments, mixing after each addition.
4. Mix with a low speed drill and 4-sided mortar paddle until thoroughly blended.

5. Additional water may be added to adjust workability. The total amount of water added shall not exceed the amounts shown in Step #2.
6. Let stand for 5 to 10 minutes, then remix / retemper for 1 minute before use.
7. The mixed material should have a thick putty consistency and not slide off the trowel when held vertically.
8. Additives are not permitted.
9. Protect from direct sun and wind.
10. Clean tools and equipment with water immediately after use. Dried materials can be mechanically removed.

APPLICATION

All surfaces shall be between 40 °F (4 °C) and 100 °F (38 °C). Surfaces shall be clean, free of dirt, oil, grease, paint, concrete sealers or curing compounds, and structurally sound. Ensure that all control and expansion joints are not covered with MaxGrip Veneer Mortar. Manufactured stone shall comply with applicable requirements of ICC-ES Acceptance Criteria AC51 or ASTM C1670. Thin brick veneer shall comply with applicable requirements of ASTM C 1088 or per the Brick Industry Association. Tile shall comply with applicable requirements of the Tile Council of North America and/or ANSI A137.1.

1. For Master Builders Solutions Adhered Drainage CI Systems, stucco brown coat, cement board, CMU, poured in place or

precast concrete substrates, apply Master Builders Solutions Wall Systems base coat or MaxGrip Veneer Mortar as a skim coat over the acceptable substrate at approximately 1/16-inch (1.6mm) thick. Apply to an area that can be covered with adhered veneer before the skim coat dries.

- For thin brick veneer units, spread MaxGrip Veneer Mortar onto the back of bricks in a continuous layer nominally 3/16"–1/4" thick and press bricks firmly into place on the substrate.

For stone veneer, apply MaxGrip Veneer Mortar to the back of clean stone veneer in a continuous layer nominally 1/4" - 3/8" thick. Press firmly in place with a twisting movement until excess material exudes from the sides of the unit. Remove excess MaxGrip Veneer Mortar between units.

For tile, installation should proceed in accordance with ANSI A 108.5 (the type and size of the tile will dictate adhesive application).

MaxGrip Veneer Mortar shall be applied and veneer installed such that the MaxGrip Veneer Mortar be free of voids.

- Allow MaxGrip Veneer Mortar to cure for 24-hours before applying pointing mortar (if used).
- Refer to respective manufacturer instructions for veneer and pointing mortar.

TECHNICAL DATA

- Working time: 1–2 hours after water has been added. Open time is affected by humidity, temperature, and other environmental conditions

LIMITATIONS

- Protect bagged materials from moisture during transportation and storage.
- Store materials in a cool, dry place. Protect from extreme heat and direct sunlight.
- Provide supplementary heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 40 °F (4 °C) prevail.
- Protect from freezing for minimum of 72-hours after installation.
- Do not apply if rain is forecast within the next 24-hours.
- Do not wet skim coat or veneer with water prior to installation.
- Per code veneer unit shall not exceed 2 5/8" (66.7 mm) in specified thickness, 36" (914 mm) in longest dimension not more than 5 ft² (0.46 m²) in total face area and shall not weigh more than 15 lbs/ft² (718 Pa).

| TEST | METHOD | CRITERIA | RESULTS |
|--|--------------|---|---|
| Compressive Strength | ASTM C 109 | N/A | 4000 psi |
| Freeze-Thaw | ASTM C 666 | Procedure A, cycles rapid freezing and thawing in water. 40 °F - 0 °F - 40 °F in not less than 2 hours and not more than 5 hours; modified using full IVS composite in place of concrete beam | > 100 cycles, no failure of MaxGrip |
| Shear Strength | ANSI A118.4 | 28 days ≥ 200 psi After 7 day water immersion ≥ 150 psi | 565 psi at 28 days 306 psi after 7 day water immersion |
| Shear Strength | ANSI A118.15 | 7 days ≥ 300 psi 28 days ≥ 400 psi After 7 days water immersion ≥ 200 psi | 487 psi at 7 days 565 psi at 28 days 306 psi after 7 day water immersion |
| Shear Bond | ASTM C482 | Minimum 50 psi | 130 psi - Directly to molded cement mortar bed specified in ASTM C482 146 psi average to Master Builders Solutions Wall Systems standard and dry base coats molded cement mortar bed specified in ASTM C482. |
| Shear Bond (full assembly test for EPS strength) | ASTM C273 | Core shear modulus of the EPS is equal to or greater than 280 psi. The 2% offset shear strength is equal to or greater than 12 psi. | Shear modulus 281.43 psi; offset shear 13.6 psi |

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.com/en-us, e-mailing your request to mbsbcst@mbcc-group.com or calling +1 (800) 433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

TECHNICAL SUPPORT

Consult Master Builders Solutions Technical Services Department at +1 (800) 589-1336 for specific recommendations concerning all other applications. Consult the Wall Systems website at www.master-builders-solutions.com/en-us, for additional information about products and systems and for updated literature.

VOC CONTENT

0 g/l, or 0 lbs/gal less water and exempt solvents.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

For the most current version of this literature, please visit our website at www.master-builders-solutions.com/en-us.