

StuccoBase

PACKAGING

36.3 kg (80 lbs) per bag

COVERAGE

Coverage may vary depending upon surface conditions and application technique.

7.43–8.36 m² (80–90 ft²) per 80 lb bag at a thickness of 3/8" to 1/2"

DESCRIPTION

Factory-blended mixture of Portland cement, reinforcing fibers, and other proprietary ingredients. StuccoBase is a concentrate which requires the addition of 90.7–108.9 kg (200–240 lbs) of plaster sand conforming to ASTM C144 or ASTM C897 and 18.9–22.7 liters (5–6 gallons) of potable water. StuccoBase conforms to ASTM C926, the standard specification for application of Portland cement-based stucco.

USES

For use with the Master Builders Solutions Stucco Wall Systems. Acceptable substrates include: PermaBase® Cement Board and other cement-boards conforming with ASTM C1325 (Type A-exterior); poured concrete/unit masonry; ASTM C1177 type sheathings including eXP™ sheathing; GlasRoc® sheathing; Securock™ glass-mat sheathing; DensGlass™ exterior sheathing; GreenGlass sheathing and Weather Defense Platinum sheathing; gypsum sheathing (ASTM C79/C1396), expanded polystyrene insulation board complying with ASTM C578 Type II with nominal 1.5 lbs/ft³ density, Exposure I or exterior plywood (Grade C/D or better), or Exposure I OSB, to which an air/water-resistive membrane and lath are attached.

MIXING

1. Use mixer which is clean and free of foreign substances.
2. Add 18.9–22.7 L (5–6 gallons) of clean potable water to mixer per bag of StuccoBase.
3. Add one bag of StuccoBase.
4. Add one half 45.4–54.4 kg (100–120 lbs) of the required plaster sand (ASTM C144 or ASTM C897).
5. Mix for 3–4 minutes at normal mixing speed while adding the remainder 45.4–54.4 kg (100–120 lbs) of the plaster sand. Allow material to set for 2–4 minutes, then remix adding water to achieve desired consistency.

ADVANTAGES

Superior weathering properties; long-term durability

Proprietary formulation; improved moisture resistance and low water absorption

Fiber reinforced; resists shrinkage cracking when properly cured

Needs only addition of water and sand; easy to mix and use with consistent results

Concentrated for use with local sand; economical

Note: Over-mixing may cause excessive air entrainment. (Due to the potential of uncontrolled air-entrainment, the use of latex polymers with StuccoBase is not recommended. Before making any on-site additions other than sand and water to StuccoBase, consult specific additive manufacturer for recommendations.)

Plaster sand must be clean and free from deleterious amounts of loam, clay, silt, soluble salts and organic matter. Sampling and testing must comply with ASTM C144 or ASTM C897. Plaster sand must be graded within the following limits

APPLICATION

1. Apply Master Builders Solutions Wall Systems' materials in accordance with current specifications and details.
2. Over wood or metal framing with sheathing, a water-resistive barrier and PermaLath, PermaLath 1000, wire fabric or self furring, expanded metal lath must be installed in accordance with ASTM C1063. When installed over wood based sheathing, two layers of grade D building paper are required or one layer of Grade D 60 minute paper with one layer of EPS or extruded polystyrene board with tongue and grooved edges or other substantially non water absorbing layer or drainage space are required, prior to installation of the lath.
3. Over concrete or masonry, remove all dust, dirt, grease, oil, laitance, efflorescence, biological residue, existing paint or coatings, curing compounds, form release agents or any other contaminants which might affect the bond. StuccoBond may be used to increase bond strength.
4. Trim accessories are installed per the project requirements and/or specifications.
5. For 9.5 mm (3/8") to 13 mm (1/2") application, apply mixed StuccoBase™ to the acceptable substrate by hand troweling or machine spraying in one coat to a minimum thickness of 9.5 mm (3/8") and a maximum thickness of 13 mm (1/2") completely embedding the lath. Use a rod and darby to level the applied base coat without exposing the lath.
- OR -
For 19 mm (3/4") to 22 mm (7/8") application, apply mixed StuccoBase first "scratch" coat to the acceptable substrate by hand troweling

or machine spraying to a minimum thickness of 9.5 mm (3/8") and a maximum thickness of 13 mm (1/2"), ensuring that the first coat is thick enough to embed the lath and allow for scoring of the surface. As soon as first coat becomes firm, score the entire surface in one direction only. Score vertical surfaces horizontally to provide key for second coat.

Apply the second "brown" coat by hand troweling or machine spraying to provide the required total thickness as soon as the first coat is rigid enough to accept it without damage to the first coat. Level surface using rod or darby. Brown coat must be uniform in thickness. Ensure that the second coat is applied over a damp first coat. The first coat and second coat combined thickness will be from 19 mm (3/4") to 22 mm (7/8"). This double back method of application is done where by the first and second coats are applied and cured as one system. Application of the second brown coat may be delayed, provided the second coat is applied over a sufficiently damp first coat.

6. After surface has sufficiently hardened, use sponge or hard rubber float as required to fill voids, holes or imperfections, leaving surface ready to receive StuccoPrime or Finish Coat.
7. Damp cure for at least 48 hours by lightly and evenly fogging the surface with water at least twice a day. Direct sunlight, hot temperatures, low humidity and wind may make additional fogging necessary.
8. Allow Base Coat to cure a minimum of 6 days prior to application of EPS insulation board shapes or primer and Finish Coat application.

LIMITATIONS

1. Surface and ambient temperatures must be between 4 °C and 36 °C (40 °F–100 °F) during the application and curing.
2. Do not install stucco under hot, dry, or windy conditions.
3. Avoid applying in direct sunlight.
4. Protect walls from rain, snow, and frost for a period of 48–72 hours; otherwise, low strength, streaking, or efflorescence may occur.
5. Expansion joints are required at least every 13m² (144 ft²), at the junction of dissimilar substrates, at existing joints in the substrate, and at floor lines in multi-level construction.
6. Do not install stucco over accessories, such as lights, bullet boxes, hose bibs.

7. Texture will vary depending upon application technique and sand type; test installations are recommended.
8. Apply StuccoBase in a continuous application within the area defined by expansion joints; always work to a wet edge to eliminate cold joints.
9. Proper application is the responsibility of the user.
10. Protect bussed materials from moisture during shipment and storage.
11. Shelf life of StuccoBase is 8 months if stored as directed.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.com/en-us, e-mailing your request to mbsbcst@mbcc-group.com or calling +1 (800) 433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

TECHNICAL SUPPORT

Consult Master Builders Solutions Technical Services Department at +1 (800) 589-1336 for specific recommendations concerning all other applications. Consult the Wall Systems website at www.master-builders-solutions.com/en-us, for additional information about products and systems and for updated literature.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict

liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

For the most current version of this literature, please visit our website at www.master-builders-solutions.com/en-us.