

## Texture Finish

100% acrylic polymer finish coat

### Product Bulletin

#### DESCRIPTION

Factory-mixed, 100% acrylic polymer finish coat. TEXTURE Finish can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel.

#### PACKAGING

31.7-kg per 19-liter pail  
(70-lbs. per 5-gallon pail)

#### COVERAGE

Varies depending upon texture

#### COLORS

Available in a wide variety of standard colors

#### HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting [www.senergy.basf.com](http://www.senergy.basf.com). Use only as directed.

#### TECHNICAL SUPPORT

Consult our Technical Services Department for specific recommendations concerning all other applications. Consult the web site, [www.senergy.basf.com](http://www.senergy.basf.com) for additional information and for updated literature.



#### USES

1. TEXTURE Finish provides an aesthetically pleasing surface color and texture for the SENERGY Wall Systems.
2. TEXTURE Finish can also be utilized as a textured coating for poured concrete or unit masonry, veneer plaster or gypsum wallboard (interior applications only), conventional stucco, SENERGY Stucco Wall System and certain insulating concrete forms.

**NOTE: If a “smooth application is required, multiple coats and skillful applications techniques will be required. Over trowelling or “burnishing” may create changes in color.**

# Texture Finish

## MIXING

1. Thoroughly mix the factory-prepared TEXTURE Finish with a mixer until thoroughly blended.
2. A small amount of clean, potable water may be added to adjust workability.
3. Additives are not permitted.
4. Close container when not in use.
5. Clean tools with soap and water immediately after use.

## APPLICATION

1. Substrate shall be dry, clean, sound and free of releasing agents, paint or other residue or coatings. Verify substrate is flat, free of fins or planar irregularities greater than 6.4 mm in 3 m (1/4" in 10').
2. Apply TEXTURE Finish directly to the Senergy Base Coat/Reinforcing Mesh with a clean, stainless steel trowel.
3. Apply and level TEXTURE Finish during the same operation, to obtain minimum 1.6 mm (1/16") thickness uniform coverage.
4. Maintain a wet edge on TEXTURE Finish by applying and texturing continually over the wall surface.
5. Work TEXTURE Finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area.
6. Float TEXTURE Finish to achieve final texture.

## LIMITATIONS

1. Protect Senergy materials during transportation and installation to avoid physical damage.
2. Store Senergy materials in a cool, dry place protected from freezing. Store at no less than 4°C (40°F). Protect from extreme heat and direct sunlight. Shelf life is two years when unopened and stored as directed.
3. Do not apply Senergy materials in ambient temperatures below 4°C (40°F). Provide supplementary heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 4°C (40°F) prevail. If using a thicker application of TEXTURE Finish, longer drying period will be required.
4. Do not apply Senergy materials to frozen surfaces.
5. Samples of TEXTURE Finish are available from Senergy for color approval only. Samples for job approval must be made in the field by the applicator, and approved prior to ordering.

## WARRANTY

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Product Bulletin, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. **BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS.** The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. In the absence of an extended warranty issued by BASF, any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. **BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.**

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

Features	Benefits
Ability to create unique surface textures	Achieve a wide variety of appearances include stipple and skip-trowel
100% Acrylic polymer chemistry	Long-term durability and weather resistance
Does not require a sealer	Save time and money
Weather resistant	Repels water and resists wind-driven rain
Breathable	Doesn't blister, peel or flake

For the most current version of this literature, please visit our website at [www.senergy.basf.com](http://www.senergy.basf.com).