

Ultra Smooth Finish

100% acrylic polymer finish coat

COLORS

Available in a wide variety of standard and custom colors.

PACKAGING

31.75-kg per 19-liter pail
(70-lbs per 5-gallon pail)

COVERAGE

First coat: 470 ft² (44 m²).
Second coat: 700 ft² (65.03 m²).
Combined two coats are approximately 280 ft² (26.01 m²). Third coat (if needed): 700 ft² (65.03 m²).

DESCRIPTION

Factory-mixed, 100% acrylic polymer finish coat. Ultra Smooth Finish utilizes a uniformly-sized particle distribution for an ultra smooth texture.

USES

1. Provides an aesthetically pleasing surface color and ultra smooth texture for Finestone Wall Systems.
2. Can also be utilized as an ultra-smooth finish for poured concrete or unit masonry, conventional stucco, certain insulating concrete forms, and interior veneer plaster or gypsum wallboard.

MIXING

Mix by using a clean spiral or Jiffiler style mixer with a low speed drill. **Do not use drywall mixing paddles!** Wipe sides of pail down with a water soaked rag to help eliminate dried particles from falling into the product. Spritz a small amount of water over unused material before replacing the lid. Replace lid when not being used.

SURFACE PREPARATION

The surface should not contain irregularities greater than 1/8 inch. All divots, pits, mesh overlaps, and mesh patterns must be leveled and skimmed with Finestone Base Coat to correct any imperfections. To ensure a smooth surface, two applications of base coat are required. **Note: All leveling corrections must be made using the base coat.**

Sand or stone the surfaces to reduce imperfections and remove trowel marks. Remove dust/debris prior to application of Master Builders Solutions Tinted Primer. Apply Master Builders Solutions Tinted Primer at a rate of 150–50 ft²/gal

PERFORMANCE CRITERIA	TEST METHOD	RESULTS
Water Vapor Transmission	ASTM E96 Method B	>30 perms (30 wet mils film thickness)
Adhesion, 7 day	ASTM D4541	>200 psi (basecoat and concrete), <50 psi (EIFS)
Wind Driven Rain Resistance	ASTM D6904	Passes, no water penetration
Surface Burning	ASTM E84	Class A rating
VOC	EPA 24	<50 g/L (less water and exempt solvents) Complies with US EPA (40 CFR 59) and South Coast AQMD (Rule 1113) VOC emission standards for architectural coatings.

RECOMMENDED TROWELS

First coat: Stainless steel tapered 12 x 4 Venetian trowel

Second coat: Stainless steel tapered 12 x 4 Venetian trowel for initial application. Flexible plastic Venetian trowel to create the final smooth appearance. Ancora makes a plastic trowel (article number 817/RS-1mm) that has been found to work well.

Note: Use of standard EIFS/stucco trowels (either new or broken-in) may result in uneven finish application.

APPLICATION

- Two coats of Ultra Smooth Finish are required. Apply the first coat of Ultra Smooth Finish using a 12 x 4 Venetian trowel at a uniform thickness of 10–15 mils. Maintain a wet edge at all times during application. Application thickness is critical. Where insufficient thicknesses are applied, discoloration and rapid drying may result. Excessive thickness may cause check cracking.
- Allow the first coat of Ultra Smooth Finish to dry and partially cure, then sand the finish with 100-150 grit sandpaper to remove trowel marks and create a smooth surface. Change sandpaper frequently. For best results, sand Ultra Smooth Finish on the same day that it is applied, before it is fully cured. Wipe the sanded surface with a damp rag to remove dust.
- Extra care is needed with power sanders. If they are used, rotate sander in a figure 8 pattern to avoid creating a sanding pattern. Avoid sanding deep holes into the Ultra Smooth Finish surface.
- For the second (and third coat if needed), a small amount of cool, clean, potable water may be used to adjust workability. **Do not add more than 15oz of water per full pail of Ultra Smooth Finish.**
- Apply the second (and third coat, if needed) in thin (8–12 mil) applications, using the stainless steel trowel. Additional trowel pressure will be needed to ensure adhesion of the second and third coats. Free style leveling is not recommended, since it can result in wavy surfaces that become evident in critical light.
- Manipulate the second finish application (or third, if needed) using the flexible plastic Venetian trowel to obtain a smooth, trowel line free application. While manipulating the thin second or third coats, be prepared to spritz the surface of Ultra Smooth Finish and the face of the trowel with clean potable water,

using a hand-held spray bottle. This will help maintain a wet edge if the finish begins to set before application is complete. Dark burnish marks from the trowel can be an indication that additional water is needed to maintain a wet surface. Manipulate the surface until it is smooth, achieving a trowel line free application. **Note: spritzing water onto dark colored Ultra Smooth Finish may cause minor discoloration.**

- If discoloration of dark colored Ultra Smooth finish is unacceptable, apply Master Builders Solutions color coat tinted to the same color as the Ultra Smooth finish to create a uniform color.
- For any color of Ultra Smooth Finish, if color uniformity is not achieved on the second coat, Master Builders Solutions Color Coat may be applied in lieu of a third coat of Ultra Smooth Finish.
- If a mottled effect is desired, use the stainless steel Venetian trowel for final leveling of Ultra Smooth Finish.

LIMITATIONS

- Protect Master Builders Solutions/Finestone materials during transportation and installation to avoid physical damage.
- Store Master Builders Solutions/Finestone materials in a cool, dry place protected from freezing. Store at no less than 40 °F (4 °C) and below 120 °F (49 °C). Protect from extreme heat and direct sunlight. Shelf life is two years when unopened and stored as directed.
- Do not apply Master Builders Solutions/Finestone materials in ambient temperatures below 40 °F (4 °C) or to frozen temperatures. Provide supplementary heat during installation and drying period (at least 24 hours after installation and until dry) when temperatures less than 40 °F (4 °C) prevail.
- Do not apply Ultra Smooth Finish in direct sun. In extreme heat and/or sun utilize a filter screen to reduce surface temperature.
- Limiting panel size to 4 ft x 6 ft (1200 mm x 1800 mm) helps create consistent aesthetic appearance.
- Product is designed for professional use only. A jobsite mock-up is highly recommended to qualify workmanship.
- Master Builders Solutions Color Coat is only used for color uniformity, it will not correct leveling issues on Ultra Smooth Finish.

TECHNICAL SUPPORT

Consult Master Builders Solutions Technical Services Department at +1 (800) 589-1336 for

specific recommendations concerning all other applications. Consult the Wall Systems website at finestone.master-builders-solutions.com/en, for additional information about products and systems and for updated literature.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting finestone.master-builders-solutions.com/en, e-mailing your request to mbsbscst@mbcc-group.com or calling +1 (800) 433-9517. Use only as directed.

IN CASE OF EMERGENCY: Call CHEMTEL +1 (800) 255-3924 or if outside the US or Canada, +1 (813) 248-0585.

LIMITED WARRANTY NOTICE

Master Builders Solutions Construction Systems US, LLC ("Master Builders") warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. MASTER BUILDERS MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of Master Builders. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. MASTER BUILDERS WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on Master Builders' present knowledge and experience. However, Master Builders assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. Master Builders reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

For the most current version of this literature, please visit our website at finestone.master-builders-solutions.com/en.