

Senerflex GDC – Section 07 24 19

Water-drainage Class PB EIFS incorporating an air/water-resistive barrier and a Geometrically Defined Drainage Cavity (GDDC)

INTRODUCTION

This specification has been assembled to enable the design professional to select or delete sections to suit the project requirements and is intended to be used in conjunction with Senergy[®] typical details, product bulletins, technical bulletins, etc.

DESIGN RESPONSIBILITY

It is the responsibility of both the specifier and the purchaser to determine if a product is suitable for its intended use. The designer selected by the purchaser shall be responsible for all decisions pertaining to design, detail, structural capability, attachment details, shop drawings and the like. The Wall Systems business of BASF Corporation (herein referred to as “BASF Wall Systems”) has prepared guidelines in the form of specifications, typical application details, and product bulletins to facilitate the design process only. BASF Wall Systems is not liable for any errors or omissions in design, detail, structural capability, attachment details, shop drawings or the like, whether based upon the information provided by BASF Wall Systems or otherwise, or for any changes which the purchasers, specifiers, designers or their appointed representatives may make to BASF Wall Systems published comments.

Designing and Detailing a SENERFLEX GDC WALL SYSTEM

General: The system shall be installed in strict accordance with current recommended published details and product specifications from the system’s manufacturer.

A. Wind Load

1. Maximum deflection not to exceed L/240 under positive or negative design loads.
2. Design for wind load in conformance with local code requirements.

B. Substrate Systems

1. Acceptable substrates are: PermaBase[®] Cement Board and other cement-boards conforming with ASTM C1325 (Type A-exterior); poured concrete/unit masonry; ASTM C1177 type sheathings, including, Weather Defense[™] Platinum sheathing, GreenGlass[®] sheathing, eXP[™] sheathing, GlasRoc[®] sheathing, Securock[™] glass-mat sheathing, and DensGlass[®] exterior sheathing DensElement (sheathing only); gypsum sheathing (ASTM C79/C1396); Huber Zip (sheathing only) Exposure I or exterior plywood (Grade C/D or better); or Exposure I OSB.
2. Painted and otherwise coated surfaces of brick, unit masonry, stucco and concrete shall be inspected and prepared as approved by BASF Wall Systems before application. The applicator shall verify that the proposed substrate is acceptable prior to the SENERFLEX GDC Wall System installation.
3. The substrate systems shall be engineered with regard to structural performance by others.

C. Moisture Control

1. Prevent the accumulation of water behind the EIFS, either by condensation or leakage through the wall construction, in the design and detailing of the wall assembly.
 - a. Provide flashing to direct water to the exterior where it is likely to penetrate components in the wall assembly, including, above window and door heads, beneath window and door sills, at roof/wall intersections, decks, abutments of lower walls with higher walls, above projecting features, and at the base of the wall and anywhere else required by local code.
 - b. Air Leakage Prevention: Provide continuity of air barrier system at foundation, roof, windows, doors and other penetrations through the system with connecting and compatible air barrier components to minimize condensation and leakage caused by air movement.
 - c. Vapor Diffusion and Condensation: Perform a dew point analysis of the wall assembly to determine the potential for accumulation of moisture in the wall assembly as a result of water vapor diffusion and condensation. Adjust insulation thickness and/or other wall assembly

Senergy Senerflex GDC Wall System

components accordingly to minimize the risk of condensation. Avoid the use of vapor retarders on the interior side of the wall in warm, humid climates.

D. Impact Resistance

1. Provide Ultra-High impact resistance to a minimum height of 1.8 m (6'- 0") above finished grade at all areas accessible to pedestrian traffic and other areas exposed to abnormal stress or potential impact. Indicate the areas with impact resistance requirements other than "Standard" on contract drawings.

E. Colour Selection

1. The use of dark colours must be considered in relation to wall surface temperature as a function of local climate conditions. Select Finish Coat colour with a light reflectance value (LRV) of 20% or higher. The use of dark colours (LRV less than 20%) is not recommended with EIFS that incorporate expanded polystyrene (EPS). EPS has a sustained service temperature limitation of approximately 71°C (160°F).

F. System Joints

1. Expansion joints in the system are required at building expansion joints, at prefabricated panel joints, floor lines of wood frame construction, where substrates change and where structural movement is anticipated. It is the sole responsibility of the project design team, including the architect, engineer, etc., to ultimately determine specific expansion joint placement, width and design. Detail specific locations in construction drawings.
2. Sealant joints are required at all penetrations through the SENERFLEX GDC (windows, doors, etc.)
3. Specify compatible closed cell backer rod and acceptable sealant that has been evaluated in accordance with ASTM C 1382, "Test Method for Determining Tensile Adhesion Properties of Sealants When Used in Exterior Insulation and Finish System (EIFS) Joints," and that meets minimum 50% elongation after conditioning.
4. The system must be properly terminated (back-wrapped a min. of 50 mm (2"), properly sealed, flashed) at all penetrations, lighting fixtures, electrical outlets, hose bibs, dryer vents, etc.

G. Grade Condition

1. The SENERFLEX GDC is not intended for use below grade or on surfaces subject to continuous or intermittent immersion in water or hydrostatic pressure. Ensure a minimum 203.2 mm (8") clearance above grade or as required by code, a minimum 25.4 mm (1") clearance above finished grade (sidewalk/concrete flatwork).

H. Trim, Projecting Architectural Features

(NOTE TO SPECIFIER: Installation of the Senergy Wall System outside the slope guidelines referenced in this specification may still qualify for a standard warranty; however, low sloping EIFS conditions are subject to extreme heat, increased maintenance and premature deterioration of the system shall be expected and any deleterious effects caused by the lack of slope will not be the responsibility of BASF Wall Systems. Senergy Wall Systems are designed and tested to be applied to vertical surfaces. The design professional has the option to build according to his/her project needs. The design professional must also consider geography, climate, building orientation, wall orientation and adjacent building components when designing with EIFS. The slope guidelines referenced below are provided to offer assistance to the owner and/or design professional. Final design of any building is the responsibility of the design professional.)

1. Minimum slope for all projections shall be 1:2 (27°) with a maximum length of 30.5 cm (12") [e.g. 15 cm in 30.5 cm (6" in 12")]. Increase slope for northern climates to prevent accumulation of ice/snow on the surface.

I. Coordination with other trades

1. Evaluate adjacent materials such as windows, doors, etc. for conformance to manufacturer's details. Adjacent trades shall provide scaled shop drawings for review.
2. Air seals at any joints/gaps between adjoining components (penetrations, etc.) are of primary importance to maintain continuity of an air barrier system and must be considered by the design professional in the overall wall assembly design. Install air seals between the primary air/water-resistive barrier and other wall components (penetrations, etc.) in order to maintain continuity of an air barrier system.
3. Provide site grading such that SENERFLEX GDC terminates a minimum of 203 mm (8") above finished grade or as required by code.

Senergy Senerflex GDC Wall System

4. Provide protection of rough openings in accordance with Senergy's *Air/Water-Resistive/Vapor Barrier Application Guidelines* before installing windows, doors, and other penetrations through the wall.
5. Install copings and sealant immediately after installation of the SENERFLEX GDC and when Senergy coatings are completely dry.

TECHNICAL INFORMATION

Consult BASF Wall Systems' Technical Services Department for specific recommendations concerning all other applications. Consult the Senergy website, www.senergy.basf.com, for additional information about products and systems and for updated literature.

Senergy Senerflex GDC Wall System

PART 1 GENERAL

NOTE TO SPECIFIER: Items in blue/underlined indicate a system option or choice of options. Throughout the specification, delete those which are not required or utilized.

1.01 SECTION INCLUDES

- A. Refer to all drawings and other sections of this specification to determine the type and extent of work therein affecting the work of this section, whether or not such work is specifically mentioned herein.
- B. SENERFLEX GDC: Composite wall of Senergy air/water-resistive barrier, adhesive, GDC insulation board, base coat, reinforcing mesh and finish coat.
- C. Senergy products are listed in this specification to establish a standard of quality. Any substitutions to this specification shall be submitted to and receive approval from the Architect at least 10 days before bidding. Proof of equality shall be borne by the submitter.
- D. The system type shall be Senergy SENERFLEX GDC wall system as manufactured by BASF Corporation - Wall Systems, Shakopee, Minnesota (herein referred to as BASF Wall Systems).

1.02 RELATED SECTIONS

- A. Section 03 00 00 Concrete substrate
- B. Section 04 00 00 Masonry substrate
- C. Section 05 40 00 Cold-formed metal framing
- D. Section 06 16 00 Sheathing
- E. Section 06 11 00 Wood framing
- F. Section 07 27 00 Air barriers
- G. Section 07 62 00 Sheet metal flashing and trim
- H. Section 07 65 00 Flexible flashing
- I. Section 07 90 00 Joint protection
- J. Section 08 00 00 Openings
- K. Section 09 22 00 Supports for plaster and gypsum board
- L. Section 09 22 16 Non-structural metal framing
- M. Section 09 29 00 Gypsum board

1.03 DEFINITIONS

- A. Exterior Insulation and Finish System: Exterior assembly comprised of GDC insulation board, adhesive, base coat, reinforcing mesh, and finish coat.
- B. Class PB Systems: A class of EIFS where the base coat varies in thickness depending upon the number of layers or thickness of reinforcing mesh. The reinforcing material is glass fibre mesh, which is embedded into the base coat at the time of installation. The base coat shall be applied so as to achieve reinforcing mesh embedment with no reinforcing mesh colour visible, nominal 1.6 mm (1/16"). Protective finish coats, of various thicknesses, in a variety of textures and colours, are applied over the base coat.
- C. Water-Drainage EIFS: A wall cladding design with an exterior surface for primary weather protection and aesthetics, which incorporates an inner air/water-resistive barrier to accommodate incidental moisture and direct it to the exterior.

1.04 SUBMITTALS

- A. Submit under provisions of Section [01 33 00]
- B. Product Data: Provide data on SENERFLEX GDC materials, product characteristics, performance criteria, limitations and durability.
- C. Code Compliance: Provide manufacturer's applicable code compliance report.
- D. Samples: Submit [two] [x] [millimeter] [inch] size samples of SENERFLEX GDC illustrating finish coat colour and texture range.
- E. Certificate: System manufacturer's approval of applicator.
- F. Sealant: Sealant manufacturer's certificate of compliance with ASTM C1382.
- G. System manufacturer's current specifications, typical details, system design guide and related product literature which indicate preparation required, storage, installation techniques, jointing requirements and finishing techniques.

Senergy Senerflex GDC Wall System

1.05 QUALITY ASSURANCE

- A. Manufacturer: More than 10 years in the EIFS industry, with more than 1000 completed EIFS projects.
- B. Applicator: Approved by BASF Wall Systems in performing work of this section.
- C. Regulatory Requirements: Conform to applicable code requirements for exterior insulation and finish system.
- D. Field Samples
 - 1. Provide under provisions of Section [\[0143 36\]](#) [\[01 43 39\]](#) [] .
 - 2. Construct one field sample panel for each colour and texture, [\[x\]](#) [\[meters\]](#) [\[feet\]](#) in size of system materials illustrating method of attachment, surface Finish, colour and texture.
 - 3. Prepare each sample panel using the same tools and techniques to be used for the actual application.
 - 4. Locate sample panel where directed.
 - 5. Accepted sample panel [\[may\]](#) [\[may not\]](#) remain as part of the work.
 - 6. Field samples shall be comprised of all wall assembly components including substrate, air/water-resistive barrier, adhesive, insulation board, base coat, reinforcing mesh, primer (if specified), finish coat, and typical sealant/flashing conditions.

1.06 DELIVERY, STORAGE AND HANDLING

- A. Deliver, store and handle products under provisions of Section [\[01 65 00\]](#) [\[01 66 00\]](#) [] .
- B. Deliver BASF Wall Systems / Senergy materials in original unopened packages with manufacturer's labels intact.
- C. Protect BASF Wall Systems / Senergy materials during transportation and installation to avoid physical damage.
- D. Store BASF Wall Systems / Senergy materials in cool, dry place protected from freezing. Store at no less than 4°C/40°F (10°C/50°F for AURORA STONE, AURORA TC-100 and ALUMINA Finish).
- E. Store rigid insulation boards flat and protected from direct sunlight and extreme heat.
- F. Store MAXFLASH at a minimum of 4°C/40°F. In cold weather, keep containers at room temperature for at least 24 hours before using.

1.07 PROJECT/SITE CONDITIONS

- A. Do not apply BASF Wall Systems / Senergy in ambient temperatures below 4°C/40°F (10°C/50°F for AURORA STONE, AURORA TC-100 and ALUMINA Finish). Provide properly vented, supplementary heat during installation and drying period when temperatures less than 4°C/40°F (10°C/50°F for AURORA STONE, AURORA TC-100 and ALUMINA Finish) prevail.
- B. Do not apply BASF Wall Systems / Senergy materials to frozen surfaces.
- C. Maintain ambient temperature at or above 4°C/40°F (10°C/50°F for AURORA STONE, AURORA TC-100 and ALUMINA Finish) during and at least 24 hours after SENERFLEX GDC installation and until dry.

1.08 SEQUENCING AND SCHEDULING

- A. Coordinate and schedule installation of SENERFLEX GDC with related work of other sections
- B. Coordinate and schedule installation of trim, flashing, and joint sealers to prevent water infiltration behind the system.

1.09 WARRANTY

- A. Provide BASF Wall Systems twelve-year limited labor, materials and drainage warranty for SENERFLEX GDC system installations under provisions of Section [\[01 70 00\]](#).
- B. Comply with BASF Wall Systems' project review requirements and notification procedures to assure qualification for warranty.

PART 2 PRODUCTS

2.01 MANUFACTURERS

- A. SENERFLEX GDC (Class PB System) manufactured by BASF Corporation.

Senergy Senerflex GDC Wall System

2.02 MATERIALS

NOTE TO SPECIFIER: Items in blue/underlined indicate a system option or choice of options. Throughout the specification, delete those which are not required or utilized. Contact BASF Wall Systems Technical Service Department for further assistance.

A. Air/Water-Resistive Barrier Components:

1. WS FIL Block Filler: (Optional) A one-component, water-based block filler designed to prepare rough, porous concrete / masonry substrates for subsequent application of Senergy fluid applied air/water-resistive barrier products
2. Air/Water-Resistive Barrier: ***(Required, Select a, b or c)***
 - a. SENERSHIELD-R: A one-component fluid-applied vapor permeable air/water-resistive barrier.
 - b. SENERSHIELD-RS: A one-component fluid-applied vapor permeable air/water-resistive barrier for use with airless spray equipment.
 - c. SENERSHIELD-VB: A one-component fluid-applied vapor impermeable air/water-resistive barrier.
3. Rough Opening and Joint Treatment: ***(Required, Select a or b)***
 - a. SHEATHING FABRIC: A spun-bonded non-woven reinforced polyester web for use with Senergy fluid applied air/weather-resistive barriers.
 - b. MAXFLASH: A one-component elastomeric material for use as a flexible flashing membrane.
4. Transitional Membrane / Expansion Joint Flashing (If selected, both a & b are required)
 - a. WS FLASH: 30-mil thick, self-sealing, self-healing composite membrane of polyester fabric and rubberized asphalt. Compatible with Senergy liquid air/weather resistive barriers.
 - b. FLASHING PRIMER: A water-based primer for use prior to application of WS FLASH on all acceptable surfaces.
5. Cold Temperature Additive:
 - a. LT ADDITIVE: Blending of LT ADDITIVE with a pail of SENERSHIELD-R/-RS/-VB enables application of these materials at temperatures as low as -4°C (25°F).

B. Adhesives/Base Coats: ***(Required, Select One or More)***

7. ALPHA Base Coat: A 100% acrylic base coat, field-mixed with Type I or Type II Portland cement. It has a creamy texture that is easily spread.
8. ALPHA DRY Base Coat: A dry-mix polymer adhesive and base coat containing Portland cement, and requiring only water for mixing.
9. XTRA-STOP Base Coat: A 100% acrylic-based, water-resistant base coat, field-mixed with Type I or Type II Portland cement.
10. ALPHA GENIE Base Coat: A 100% acrylic, fiber-reinforced base coat, adhesive and leveler that is field-mixed with Type I or Type II Portland cement.

NOTE TO SPECIFIER: Portland cement is not required if ALPHA DRY Base Coat is specified.

C. Portland cement: Conform to ASTM C150, Type I, II, or I/II, grey or white; fresh and free of lumps.

D. Water: Clean and potable without foreign matter.

E. Rigid Insulation Board:

1. Expanded polystyrene; conform to CAN/ULC-S701; Flame spread between 25 and 500 per CAN/ULC-S102; average density 16 kg/m³ (1 lb/ft³); K=6.09 per mm (0.24 per inch); 38 mm (1 1/2") thickness minimum as indicated on drawings; geometric drainage cavity dimensions as specified in current Senergy details, meeting the following:
 - a. Air-dried (aged) five weeks, or kiln dried or equivalent, prior to installation.
 - b. Edges: square within 0.8 mm per meter (1/32" per foot).
 - c. Thickness: tolerance of plus or minus 1.6 mm (1/16").
 - d. Size: 0.6 m x 1.22 m (2' x 4').
 - e. Length and width: tolerance of plus or minus 1.6 mm (1/16").

F. Senergy Reinforcing Mesh: A balanced, open-weave glass, fiber reinforcing mesh, twisted multi-end strands treated for compatibility with Senergy Base Coats. ***(Required, Select One or More)***

1. FLEXGUARD 4: Standard weight, 4 oz.
2. INTERMEDIATE 6: Standard/medium weight, 6 oz.
3. INTERMEDIATE 12: Intermediate weight, 12 oz.
4. STRONG 15: Heavy weight, 15 oz. used only in combination with FLEXGUARD 4 or INTERMEDIATE 6.

Senergy Senerflex GDC Wall System

5. HI-IMPACT 20: Heavy weight, 20 oz. used only in combination with FLEXGUARD 4 or INTERMEDIATE 6.
6. CORNER MESH: Intermediate weight, pre-marked for easy bending, for reinforcing at exterior corners.
- G. **BASF COLOR COAT Coating: (Optional)** A 100% acrylic-based coating. It is designed for spray-, roller- or brush-application over EIFS with minimum change in finish texture or sheen.
- H. **BASF TINTED PRIMER: (Optional)** A 100% acrylic-based primer that helps alleviate shadowing and enhances performance of the Senergy Wall Systems. Color to closely match the selected Senergy Finish Coat color.
- I. **Senergy Finish Coat: (Required, Select One or More Finishes and Textures)**
 1. SENERFLEX Finish: 100% acrylic polymer finishes with advanced technology to improve long-term performance and dirt pick-up resistance; air cured, compatible with base coat; Senergy finish color [] as selected; finish texture:
 - a. CLASSIC: Has a medium “worm-holed” appearance which is achieved by the random aggregate sizes in the Finish. The “worm-holed” look can be circular, random, vertical or horizontal.
 - b. FINE: utilizes uniformly-sized aggregates for a uniform, fine texture.
 - c. TEXTURE: can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel
 - d. SAHARA: Provides a uniform, “pebble” appearance.
 2. SENERFLEX TERSUS Finish: Modified acrylic based finish with water repellent properties, compatible with base coat; Senergy Finish color [] as selected; finish texture:
 - a. F1.0: A 1.0 mm uniform aggregate creating a fine texture.
 - b. M1.5: A 1.5 mm uniform aggregate creating a medium sand texture.
 - c. T0.5: can achieve a wide variety of free-formed, textured appearances, including stipple and skip-trowel
 - e. R1.5: Has a medium “worm-holed” appearance which is achieved by the random aggregate sizes in the Finish. The “worm-holed” look can be circular, random, vertical or horizontal.
 3. Specialty Finishes: 100% acrylic polymer finishes that can be hand-troweled to simulate stone or create a time-honored, mottled tone-on-tone look that achieves a soft and weathered patina over time.
 - a. ENCAUSTO VERONA: Utilizes uniformly-sized aggregate to achieve a free-formed, flat texture. It can be used to achieve a mottled look and unlimited tone on tone designs by combining multiple colors.
 - b. METALLIC: Has a pearlescent appearance. It utilizes uniformly-sized aggregates for a uniform fine texture.
 - c. AURORA TC-100: Provides a stone-like appearance, either rough or smooth depending upon application.
 - d. AURORA STONE: Provides a rough, stone-like appearance.
 - e. ALUMINA: Is a factory-mixed, reflective stone finish consisting of colored aggregate and large black mica flakes in a 100% acrylic transparent binder that provides a classic granite or marble-like textured finished appearance.
 4. CHROMA Finish: 100% acrylic polymer based finish with integrated high performance colorants for superior fade resistance, compatible with base coat; Senergy Finish color [] as selected; finish texture:
 - a. F1.0: Utilizes uniformly-sized aggregates for a uniformly fine texture.
 - b. M1.5: Provides a uniform “pebble” appearance.
 - c. R1.5: Has a medium “worm-holed” appearance which is achieved by the random aggregate sizes in the Finish. The “worm-holed” look can be circular, random, vertical or horizontal
- J. **BASF ANTICOGLAZE Glaze/Stain: (Optional)** 100% acrylic antiquing stain product used to impart an 'old world' mottled look to textured finishes.

2.03 ACCESSORIES

- A. **Window/Door Drip Edge:** Rigid polyvinyl chloride (PVC), UV resistant for exterior use, with a drip edge, as furnished by Plastic Components, Inc. or equal. Accessories shall conform to ASTM D1784, C1063 and D4216.

Senergy Senerflex GDC Wall System

PART 3 EXECUTION

3.01 EXAMINATION

A. Site Conditions: Verify project site conditions under provisions of Section [01 00 00] [].

B. Walls

1. Substrates:
 - a. Acceptable substrates are: PermaBase[®] Cement Board and other cement-boards conforming with ASTM C1325 (Type A-exterior); poured concrete/unit masonry; ASTM C1177 type sheathings, including, Weather Defense[™] Platinum sheathing, GreenGlass[®] sheathing, eXP[™] sheathing, GlasRoc[®] sheathing, Securock[™] glass-mat sheathing, and DensGlass[®] exterior sheathing. DensElement (sheathing only); gypsum sheathing (ASTM C79/C1396); Huber Zip (sheathing only); Exposure I or exterior plywood (Grade C/D or better); or Exposure I OSB. Consult the BASF Wall Systems Technical Services Department for all other applications.
 - b. Wall sheathing must be securely fastened per applicable building code and sheathing manufacturer's requirements.
 - c. Examine surfaces to receive SENERFLEX GDC and verify that substrate and adjacent materials are dry, clean, sound, and free of releasing agents, paint, or other residue or coatings. Verify substrate is flat, free of fins or planar irregularities greater than 6.4 mm in 3 m (1/4" in 10').
2. Flashings:
 - a. All flashings are by others and must be installed in accordance with specific manufacturer's requirements. Where appropriate, end-dams must be provided.
 - b. Openings must be flashed prior to window/door, HVAC, etc. installation. Refer to WS FLASH product bulletin and Senergy's *Moisture Protection Guidelines for Senerflex Wall Systems* bulletin for further information.
 - c. Windows and openings shall be flashed according to design and Building Code Requirements.
 - d. Individual windows that are ganged to make multiple units require continuous head flashing and the joints between the units must be fully sealed.
3. Roof:
 - a. Verify that all roof flashings have been installed in accordance with the guidelines set by the Asphalt Roofing Manufacturers Association (ARMA).
4. Kick-out flashing:
 - a. Kick-out flashing must be installed leak-proof and angled (min 100°) to allow for proper drainage and water diversion.
 - b. Do not proceed until all unsatisfactory conditions have been corrected.

3.02 PREPARATION

- A.** Protect all surrounding areas and surfaces from damage and staining during application of SENERFLEX GDC.
- B.** Protect finished work at end of each day to prevent water penetration.
- C.** Substrate preparation: Prepare substrates in accordance with Senergy instructions.

3.03 MIXING

General: No additives are permitted unless specified in product mixing instructions. Close containers when not in use. Prepare in a container that is clean and free of foreign substances. Do not use a container which has contained or been cleaned with a petroleum-based product. Clean tools and equipment with water immediately after use. Dried material can only be removed mechanically.

NOTE TO SPECIFIER: Keep only the products in this section which were selected in Section 2.02. Delete those not to be utilized.

A. Air/Water-Resistive Barriers:

1. WS FIL & SENERSHIELD-R/RS/VB: Mix with a clean, rust-free paddle and drill until thoroughly blended. Do not add water.
2. Cold Temperature Additive: LT ADDITIVE: Pour the entire contents of one (1) bottle of LT ADDITIVE into one (1) full pail of SENERSHIELD-R/RS/VB. For WS FIL, add ½ of one bottle of LT ADDITIVE per pail of WS FIL. Mix with a clean, rust-free paddle and drill until fully blended.

B. Senergy Base Coat:

1. ALPHA Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one-part (by weight) Portland cement with one-part base coat.

Senergy Senerflex GDC Wall System

Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.

2. XTRA-STOP Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one-part (by weight) Portland cement with one-part base coat. Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.
 3. ALPHA GENIE Base Coat: Mix base coat with a clean, rust-free paddle and drill until thoroughly blended, before adding Portland cement. Mix one-part (by weight) Portland cement with one-part base coat. Add Portland cement in small increments, mixing until thoroughly blended after each additional increment. Clean, potable water may be added to adjust workability.
 4. ALPHA DRY Base Coat: Mix and prepare each bag in a 19-liter (5-gallon) pail. Fill the container with approximately 5.6-liters (1.5-gallons) of clean, potable water. Add ALPHA DRY Base Coat in small increments, mixing after each additional increment. Mix ALPHA DRY Base Coat and water with a clean, rust-free paddle and drill until thoroughly blended. Additional ALPHA DRY Base Coat or water may be added to adjust workability.
- C. BASF COLOR COAT:** Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.
- D. BASF TINTED PRIMER:** Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.
- E. Senergy Finishes:**
1. SENERFLEX, SENERFLEX TERSUS, CHROMA, and ENCAUSTO VERONA Finish: Mix the factory-prepared material with a clean, rust-free paddle and drill until thoroughly blended. A small amount of clean, potable water may be added to adjust workability. Do not overwater.
- F. Specialty Finishes:**
1. AURORA TC-100, AURORA STONE, and ALUMINA Finish: Gently mix the contents of the pail for 1 minute using a low RPM ½" drill equipped with a mixing paddle such as a Demand Twister or a Wind-Lock B-MEW, B-M1 or B-M9.
- G. BASF ANTICOGLAZE Glaze/Stain:** Mix the contents of the pail with a slow speed drill and paddle mixer until thoroughly blended.

3.04 APPLICATION

A. Accessories:

1. Attach Window/Door Drip Edge level and per manufacturer's instructions.

NOTE TO SPECIFIER: Keep only the products in this section which were selected in Section 2.02. Delete those not to be utilized.

B. Air/Water-Resistive Barrier:

1. Apply the WS FIL in accordance with BASF WS FIL product bulletin
2. All sheathing joints and windows/openings must be protected, and the air/water-resistive barrier applied in accordance with *Air/Water-Resistive/Vapor Barrier Application Guideline* technical bulletin.
3. Substrate shall be dry, clean, sound, and free of releasing agents, paint, or other residue or coatings. Verify substrate is flat, free of fins or planar irregularities greater than 6.4 mm in 3 m (¼" in 10').
4. Unsatisfactory conditions shall be corrected before application of the Senergy air/water-resistive barriers.
5. Apply the SHEATHING FABRIC and Senergy air/water-resistive barrier in accordance with the Senergy air/water-resistive barrier product bulletin.
6. Apply the MAXFLASH in accordance with BASF MAXFLASH product bulletin.
7. Installed materials shall be checked before continuing system application.
8. Ensure SHEATHING FABRIC embedded in Senergy air/water-resistive barrier or BASF MAXFLASH overlaps the top flange of flashing.
9. Installed materials shall be checked before continuing system application.

C. Rigid Insulation Board:

1. Vertical surfaces: Begin at base from firm, permanent, or temporary support.

Senergy Senerflex GDC Wall System

2. Apply horizontally in a running bond pattern. Channels will be oriented vertically, parallel to the 0.6m (2') dimension.
3. Pre-cut insulation board to fit openings and projections. Insulation board must be a single piece around corners of openings. Stagger vertical joints and corners. Stagger insulation and sheathing board joints.
4. Apply mixed selected Senergy Base Coat to entire surface of insulation board using a stainless steel trowel with 13 mm x 13 mm (1/2"x 1/2") notches spaced 50 mm (2") apart. Ribbons of adhesive must be applied parallel to the 0.6m (2') dimension of the insulation board between the channels to ensure they are vertical when the insulation board is applied to the substrate.
5. Immediately set board into place and apply pressure over entire surface of board to ensure positive uniform contact and high initial grab. Do not slide board into place. Do not allow adhesive to dry prior to installing.
6. Abut all joints tightly and ensure overall flush level surface.
7. Check adhesion periodically by removing a board prior to set. Properly installed insulation board will be difficult to remove, and adhesive will be adhered to both the selected Senergy Air/Water-Resistive Barrier and the insulation board.
8. Fill 1/16" and larger gaps between insulation boards with slivers of insulation board.
9. Allow application of insulation board to dry (normally 8 to 10 hours) prior to application of base coat/reinforcing mesh.
10. Rasp flush any irregularities of the insulation board greater than 1.6 mm (1/16").
11. Install expansion joints and aesthetic grooves as indicated on drawings. Do not align aesthetic grooves with insulation board joints.

D. Senergy Base Coat/Reinforcing Mesh:

1. Base coat shall be applied to achieve reinforcing mesh embedment with no reinforcing mesh color visible.

NOTE TO SPECIFIER: Indicate on drawings the required locations of standard, medium, high or ultra-high impact reinforcing mesh.

E. Senergy CORNER MESH:

1. Install CORNER MESH at corners.
2. Apply CORNER MESH prior to application of reinforcing mesh.
3. Cut CORNER MESH to workable lengths.
4. Apply mixed Senergy Base Coat to insulation board at outside corners using a stainless-steel trowel.
5. Immediately place CORNER MESH against the wet base coat and embed the CORNER MESH into the base coat by troweling from the corner; butt edges and avoid wrinkles.
6. After base coat is dry and hard, apply a layer of FLEXGUARD 4, INTERMEDIATE 6 or 12 Reinforcing Mesh over the entire surface of the CORNER MESH in accordance with 3.04 F.

F. Standard Impact or Medium Impact Resistance Reinforcing Mesh: FLEXGUARD 4 INTERMEDIATE 6 and INTERMEDIATE 12

1. Install Senergy Reinforcing Mesh where indicated on drawings.
2. Apply mixed Senergy Base Coat to entire surface of insulation board with a stainless-steel trowel to embed the reinforcing mesh.
3. Immediately place Senergy Reinforcing Mesh against wet base coat and embed the reinforcing mesh into the base coat by troweling from the center to the edges.
4. Lap reinforcing mesh 64 mm (2 1/2") minimum at edges.
5. Ensure reinforcing mesh is continuous at corners, void of wrinkles and embedded in base coat so that no reinforcing mesh color is visible.
6. If required, apply a second layer of base coat to achieve total nominal base coat/reinforcing mesh thickness of 1.6 mm (1/16").
7. Allow base coat with embedded reinforcing mesh to dry hard (normally 8 to 10 hours).

G. High Impact or Ultra High Impact Resistance Reinforcing Mesh: INTERMEDIATE 12, STRONG 15 and HI-IMPACT 20

NOTE TO SPECIFIER: Where STRONG 15 or HI-IMPACT 20 is specified, FLEXGUARD 4 or INTERMEDIATE 6 must be specified also.

1. Install Senergy Reinforcing Mesh where indicated on drawings.
2. Apply mixed Senergy Base Coat to entire surface of insulation board with a stainless-steel trowel to

Senergy Senerflex GDC Wall System

embed the reinforcing mesh.

3. Immediately place Senergy Reinforcing Mesh against wet base coat and embed the reinforcing mesh into the base coat by troweling from the center to the edges.
4. Butt Senergy Reinforcing Mesh at all adjoining edges; do not use to backwrap or bend around corners.
5. Butt Senergy Reinforcing Mesh at adjoining edges of CORNER MESH.
6. Ensure reinforcing mesh is free of wrinkles and embedded in base coat so that no reinforcing mesh color is visible.
7. After base coat with embedded reinforcing mesh is dry and hard (normally 8 to 10 hours), apply a layer of FLEXGUARD 4 or INTERMEDIATE 6 Reinforcing Mesh over the entire surface in accordance with 3.04 F to achieve total nominal base coat/ reinforcing mesh thickness of 2.4 mm (3/32").

H. BASF COLOR COAT:

1. Apply material to the base coat/reinforcing mesh in sealant joints with a high-quality, latex-type paintbrush.
2. Work material continuously until a uniform appearance is obtained.
3. Allow to dry thoroughly (approximately 24 hours) prior to application of sealant primer and sealant.

I. BASF TINTED PRIMER:

1. Apply BASF TINTED PRIMER to the base coat/reinforcing mesh with a sprayer, 10 mm (3/8") nap roller, or good quality latex paint brush at a rate of approximately 3.6–6.1m² per liter (150–250 ft² per gallon).
2. BASF TINTED PRIMER shall be dry to the touch before proceeding to the Senergy Finish coat application.

J. Senergy Finish Coat: SENERFLEX, SENERFLEX TERSUS and CHROMA.

1. Apply Senergy Finish directly to the base coat with a clean, stainless steel trowel.
2. Apply and level Senergy Finish during the same operation to minimum obtainable thickness consistent with uniform coverage.
3. Maintain a wet edge on Senergy Finish by applying and texturing continually over the wall surface.
4. Work Senergy finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area.
5. Float Senergy Finish to achieve final texture.

K. Specialty Finish:

1. AURORA TC-100 Finish:
 - a. Apply BASF TINTED PRIMER to substrate in accordance with current BASF TINTED PRIMER product bulletin.
 - b. BASF TINTED PRIMER shall be of corresponding color for selected AURORA TC-100 Finish color. Allow BASF TINTED PRIMER to dry to the touch before proceeding to AURORA TC-100 Finish application.
 - c. Apply a tight coat of finish with a clean, stainless steel trowel.
 - d. Maintain a wet edge on finish by applying and leveling continually over the wall surface.
 - e. Work finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area. Allow first coat to set until surface is completely dry prior to applying a second coat of finish.
 - f. For a smooth appearance, use a stainless-steel trowel and apply the second coat of finish. Achieve final texture using circular motions.
 - g. For a textured appearance, apply the second coat of finish using a spray gun and hopper. Double-back to achieve final texture.
 - h. Total thickness of finish shall be approximately 1.6 mm (1/16").
2. AURORA STONE Finish:
 - a. Apply BASF TINTED PRIMER to substrate in accordance with current BASF TINTED PRIMER product bulletin.
 - b. BASF TINTED PRIMER shall be of corresponding color for selected AURORA STONE Finish color. Allow BASF TINTED PRIMER to dry to the touch before proceeding to AURORA STONE Finish application.
 - c. Apply a coat of AURORA STONE Finish using a spray gun and hopper, maintaining a wet edge. Work to corners, joints or other natural breaks and do not allow material to set up within an

Senergy Senerflex GDC Wall System

uninterrupted wall area.

- d. Allow first coat of AURORA STONE Finish to set until surface is completely dry prior to applying a second coat of AURORA STONE Finish.
- e. Apply a second coat of AURORA STONE Finish using a spray gun and hopper; double back to achieve final texture.
- f. Thickness of AURORA STONE Finish may vary between 1.6 mm (1/16") and 3.2 mm (1/8"), depending upon texture.

Note: Spraying of AURORA STONE shall be in the same manner and direction and by the same mechanic on a particular elevation or project whenever possible, to maintain a uniform appearance. Maintain consistent air pressure to minimize texture variations. Stator or rotor design pumps are not recommended.

3. ALUMINA Finish:

- a. Apply BASF TINTED PRIMER to substrate in accordance with current BASF TINTED PRIMER product bulletin.
- b. BASF TINTED PRIMER shall be of corresponding color for selected ALUMINA Finish color. Allow BASF TINTED PRIMER to dry to the touch before proceeding to ALUMINA Finish application.
- c. Apply a tight coat of finish with a clean, stainless steel trowel.
- d. Maintain a wet edge on finish by applying and leveling continually over the wall surface.
- e. Work finish to corners, joints or other natural breaks and do not allow material to set up within an uninterrupted wall area. Allow first coat to set until surface is completely dry prior to applying a second coat of finish
- f. Use a stainless-steel trowel and apply the second coat of finish. Achieve final texture using circular motions
- g. Total thickness of finish may be between 1.6 mm (1/16") and 3.2 mm (1/8").

- L. BASF ANTICOGLAZE Glaze/Stain:** Apply in accordance with recommendations contained in current product literature.

3.05 CLEANING

- A. Clean work under provisions of Section [01 74 00] [].
- B. Clean adjacent surfaces and remove excess material, droppings, and debris.

3.06 PROTECTION

- A. Protect base coat from rain, snow and frost for 48–72 hours following application.
- B. Protect installed construction under provisions of Section [01 76 00] [].

END OF SECTION

Senergy Senerflex GDC Wall System

WARRANTY

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Product Bulletin, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. **BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS.** The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is shipment to purchaser of product equal to the amount of product that fails to meet this warranty or refund of the original purchase price of product that fails to meet this warranty, at the sole option of BASF. In the absence of an extended warranty issued by BASF, any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. **BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.**

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third-party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.