

MasterSeal® M 866 (Formerly known as Mastertop® Membrane 23)

A tough elastic two component polyurethane membrane

DESCRIPTION

MasterSeal® M 866 is a two component solvent free polyurethane coating suitable for use in traffic coating systems to provide crack bridging and waterproofing capability. When used in car park decking systems it will bridge dynamic cracks.

PRIMARY USES

MasterSeal® M 866 is used primarily as a durable elastic membrane in polyurethane coating systems for car parks.

ADVANTAGES

- Tough
- Elastic
- Aggregate scatter does not sink through the wet coat.

PACKAGING

MasterSeal® M 866 is supplied in 30kg units.

COVERAGE

From 0.5kg/m² to 1.5kg/m² dependent upon application. Contact BASF SA Technical Department for clarification prior to application.

STANDARDS

ASTM C957

TYPICAL PROPERTIES*

Pot Life at 25°C	45 minutes
Tensile strength ASTM C957	6N/mm ²
Elongation ASTM C957	100%

GUIDE TO APPLICATION

APPLICATION TEMPERATURE

The quality of the final finish is dependent on the substrate and the material temperatures, we recommend a substrate temperature of min. +10°C and max. +35°C.

SURFACE PREPARATION

The surface to be coated must be clean, dry free of laitance, oil, grease or any substance that may impair adhesion.

The preferred method of surface preparation are; captive blasting, surface grinding or similar.

Weak or damaged concrete must be removed, then replaced with a suitable repair compound from the **MasterEmaco®** or **MasterBrace®** range of products.

Surface conditioning / priming

The prepared surface must be conditioned to receive the **MasterSeal® M 866** by the application of **MasterTop® 1200** surface conditioner / sealer applied at the rate of 0.15-0.30kg/m² depending on the absorption of the concrete substrate.

MIXING

Mix the complete contents of the A and B components of **MasterTop® 1200** together thoroughly.

Do not mix more primer than can be used within 15 minutes at 25°C. See datasheet **MasterTop® 1200**.

Apply the mixed material by paint roller, brush or airless spray.

Into the wet coating, broadcast **MasterTop® SR 3** at the minimum rate of 0.6kg/m² do not apply to excess, but do not leave bald areas.

Allow to cure for minimum 6 hours with a substrate temperature of 25°C or 3 hours at 40°C. Remove loose aggregate by vacuuming cleaning or sweeping. Scrape the edge of a trowel over the surface to remove aggregate that may be standing too proud of the surface.



We create chemistry

MasterSeal[®] M 866 (Formerly known as Mastertop[®] Membrane 23)

MIXING FOR MASTERSEAL[®] M 866

Mix the A and B components of the **MasterSeal[®] M 866** together using a slow speed (400 rpm) drill with a spiral mixing head. Work the mixer round the mixing pail to ensure it scrapes the side and bottom of the pail. Pour the part mixed material into a clean pail and re-mix for a further 30 seconds.

APPLICATION

Pour the mixed material onto the floor and spread at the required coverage using pin screed or trowel.

Into the wet **MasterSeal[®] M 866**, broadcast aggregate **MasterTop[®] SR 3** to excess.

Allow to cure for 24 hours at 25°C.

Remove excess aggregate by sweeping or vacuuming.

TOPCOAT

Apply a minimum of 0.8kg/m² (total) of **MasterSeal[®] TC 258** in two coats.

STORAGE

Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air conditioned environment.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

QUALITY AND CARE

All products originating from BASF Construction Chemicals South Africa are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, 2008.

* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.

BASF Construction Chemicals South Africa (Pty) Ltd

852 Sixteenth Road, Midrand

PO Box 2803, Halfway House, 1685

Tel: +27 11 203 2405

Fax: +27 11 203 2679

www.master-builders-solutions.basf.co.za