

Second generation high range water reducing polycarboxylate ether admixture for ready-mix concrete with high slump retention and a low W/C. It is suitable for hot weather conditions.

Material description

MasterGlenium SKY 698 is an innovative second generation superplasticizer of polycarboxylic ether (PCE) polymers. It is derived directly from the Total Performance Control $^{\text{TM}}$ concept.

MasterGlenium SKY 698 is specially engineered for ready-mix Rheoplastic concrete having fluid consistence and self-compacting concrete, having a very high workability retention (> 90 minutes), especially under hot weather conditions. The fresh concrete shows no segregation and at the same time has a low water cement ratio and, consequently, high early and long term strengths as per EN 206-I standards.

MasterGlenium SKY 698 may be used also to produce Rheodynamic concrete, capable of self compaction, even in the presence of dense reinforcement, without the aid of vibration.

MasterGlenium SKY 698 is chloride free, meets EN 934-2, and it is compatible with all cements meeting the EN 197-1 standards

Total Performance Control™

The Total Performance Control™ concept ensures that readymix producers, contractors and engineers get a concrete that is of the same high quality as originally specified; starting from production at the batching plant, to the delivery and placing into the formworks and followed by its hardening process. Utilizing Rheodynamic™ concrete technology it provides a concrete mix with exceptional placing characteristics and accelerated cement hydration for early strength development and high-quality concrete.

The chemistry of MasterGlenium SKY

The Total Performance ControlTM concept is the result of years of study of an in-house expertise in nanotechnology. This allows Master Builders Solutions to control the chemical and physical behaviour of polymers and their interactions with cement. MasterGlenium SKY 698 is an innovative second generation superplasticiser of polycarboxylic ether (PCE)

polymers. The dispersion effect of superplasticizers is based on the adsorption of molecules on cement particles, imparting a negative charge that causes electrostatic repulsion and steric hindrance between them and, therefore, causing dispersion. The hydration, and particularly the ettringite formation, works against the superplasticiser.

The molecules already adsorbed are covered by the ettringite lawn and thus are ineffective.

The particular configuration of the MasterGlenium SKY molecules allows its delayed adsorption onto the cement particles and disperses them efficiently over a long period of time. The molecular structure is essential for the early development of strength. With superplasticizers based on conventional polycarboxylate ether, the molecules cover the entire surface of the cement grain and build a barrier against contact with water. Therefore, the hydration process takes place slowly. The MasterGlenium SKY molecules on the other hand leave sufficient surface of the cement exposed to allow contact with water for a rapid hydration reaction which results in high early strength development.

Benefits for Ready-mix producer

Total Performance Control and the use of MasterGlenium SKY 698 offers the following benefit to the ready-mix concrete producer:

- Reduction the water content with respect to the state of the art polycarboxylate based superplasticisers.
- Production of Rheoplastic and Rheodynamic concrete having a very low W/C.
- Workability retention for a longer period especially in hot weather conditions avoiding the problem of re-tempering with water before the pouring operation.
- Improvement of the rheology even in concrete mixes having a low fines content.
- Optimization of the production of durable concrete as per the EN 206-1 and UNI 11104 standards.
- As compared to the traditional superplasticisers, the engineering properties such as early and ultimate compressive and flexural strengths, bond to steel, and modulus of elasticity, shrinkage, creep, and impermeability are improved.




Second generation high range water reducing polycarboxylate ether admixture for ready-mix concrete with high slump retention and a low W/C. It is suitable for hot weather conditions.

Compatibility

In order to optimise some special properties of the concrete, use of the following complementary admixtures is suggested:

- air entraining agent MasterAir to improve freeze thaw resistance (exposure class XF1 to XF4, EN 206-1);
- silica fume, MasterLife MS 610, for high performance concrete and to improve the durability in chemical aggressive environments (exposure class XAI to XA3, EN 206-I)
- synthetic micro-fibres MasterFiber to prevent cracks due to plastic shrinkage;
- curing agent MasterKure for sealing the surface of freshly finished concrete against rapid evaporation of water which may cause plastic shrinkage cracking.
- demoulding agent MasterFinish for good surface appearance.

In compliance with the European Regulation (EU No 305/2011 and EU No. 574/2014) the product is provided with the CE marking according to UNI EN 934-2 and the relative DoP (Declaration of Performance).



Dosage

MasterGlenium SKY 698 The recommended dosage can range from 0.8 to 1.6 litres per 100 kg of binder.

Other dosages may be recommended in special cases according to specific job site conditions.

In such cases please consult our Technical Service Department for advice.

Packaging and storage

MasterGlenium SKY 698 is available in 10 litre cans, 1.000 litre container or in bulk.

MasterGlenium SKY 698 must be stored in a place where the temperature does not drop below 5 $^{\circ}$ C. In case of freezing, warm up and homogenise the admixture solution before using.

Directions for use

MasterGlenium SKY 698 is a liquid admixture to be added to the concrete during the mixing process:

- mix cement and secondary binders, sand, coarse aggregates and the mix water until a stiff, yet homogeneous, mixture is obtained;
- optimal mixing water reduction is obtained if MasterGlenium SKY 698 is mixed into the concrete right after the addition of the initial 80-90% of the total water;
- avoid adding the admixture to the dry aggregates;
- add MasterGlenium SKY 698 admixture and mix again for to 60 seconds in order to disperse it homogeneously;
- continue mixing until required workability is obtained, with addition of the remaining water.

Compatibility

MasterGlenium SKY 698 is not compatible with all ad-mixtures of MasterRheobuild series.

Safety information

For information on the correct and safe use, transport, storage and disposal of the product, consult the most recent Safety Data Sheet.



Second generation high range water reducing polycarboxylate ether admixture for ready-mix concrete with high slump retention and a low W/C. It is suitable for hot weather conditions.

Technical Information	
Form	Liquid
Relative density (g/cc at 20°C)	1.082 – 1.112
Essential characteristic in accordance to EN 934-2	Performance
Chloride ion content	≤ 0.1% by mass
Alkali content (Na2O equivalent)	≤ 5.0%
Corrosion behaviour	Contains component only from EN 934-1: 2008 Annex A. I
Compressive strength	Equal consistence: 7 days \geq 100%; 28 days \geq 115% Equal w/c ratio: 28 days \geq 90%
Air content	Equal consistence: $\leq 2.0 \%$ Equal w/c ratio: $\leq 2.0 \%$
Water reduction	≥ 12%
Setting time	Initial: test mix \geq control mix + 90 min Final: test mix \leq control mix + 360 min
Consistency	Retention: comply 1.2 ()

Other services

For additional technical information, brochures, references, technical reports and technical support please visit www.master-builders-solutions.com/it-it or alternatively contact infomac@masterbuilders.com.

Scan QR code to visit the product page and download the latest version of this technical data sheet and any additional documentation.





Second generation high range water reducing polycarboxylate ether admixture for ready-mix concrete with high slump retention and a low W/C. It is suitable for hot weather conditions.

Disclaimer

Since 16/12/1992, Master Builders Solutions Italia Spa has been operating under a Certified Quality System compliant with the UNI EN ISO 9001 Standard. Furthermore, the Environmental Management System is certified according to the UNI EN ISO 14001 Standard and the Safety Management System is certified according to the UNI ISO 45001 Standard.

For further information, please consult the local Technician of Master Builders Solutions. The technical advice on how to use our products, either written or verbally given, are based on the current state of our scientific and practical expertise, and does not imply the assumption of any guarantee and/or responsibility for the final results of works executed using our products.

Therefore, the customer is not exempted from the exclusive task and responsibility of verifying the suitability of our products for the intended use and purposes.

This version supersedes all the previous ones.

Master Builders Solutions Italia Spa

Via Vicinale delle Corti, 21 – 31100 Treviso – Italia T +39 0422 429200 F +39 0422 421802 www.master-builders-solutions.com/it-it e-mail: infomac@masterbuilders.com